

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2001-055554

(43)Date of publication of application : 27.02.2001

(51)Int.Cl.

C09J183/04
C09D183/04
H01L 21/283
H01L 21/312
H01L 21/768

(21)Application number : 11-234603

(71)Applicant : JSR CORP

(22)Date of filing : 20.08.1999

(72)Inventor : NISHIKAWA MICHINORI
TSUNODA MAYUMI
EBISAWA MASAHIKO
HAKAMAZUKA SATOKO
YAMADA KINJI

(54) FILM-FORMING COMPOSITION AND INSULATING FILM-FORMING MATERIAL

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a film-forming composition which excels in the mechanical properties of a coated film and can effect firing of the coated film in a short period of time and exhibits a very low dielectric constant as the interlaminar insulating film material in semiconductor elements and the like.

SOLUTION: A film-forming composition contains (A) a hydrolyzate and/or a condensate of at least one compound selected from (A-1) compounds represented by formula I: $R1aSi(OR2)4-a$ (wherein R1 is hydrogen, fluorine or a monovalent organic group; R2 is a monovalent organic group; and (a) is an integer of 0-2) and (A-2) compounds represented by formula II: $R3b(R4O)3-bSi-(R7)d-Si(OR5)3-cR6c$ (wherein R3, R4, R5 and R6 are the same or different and each is a monovalent organic group; (b) and (c) are the same or different and each is a number of 0-2; R7 is an oxygen atom or $-(CH2)_n-$; (n) is 1-6; and (d) is 0 or 1), (B) a latent acid catalyst and/or a latent base catalyst, and (C) a solvent having a boiling point at normal pressures of not lower than 180° C.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

(19) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11) 特許出願公開番号

特開2001-55554

(P2001-55554A)

(43) 公開日 平成13年2月27日 (2001.2.27)

(51) Int.Cl. ⁷	識別記号	F I	ノート (参考)
C 0 9 J 183/04		C 0 9 J 183/04	4 J 0 3 8
C 0 9 D 183/04		C 0 9 D 183/04	4 J 0 4 0
H 0 1 L 21/283		H 0 1 L 21/283	P 4 M 1 0 4
21/312		21/312	C 5 F 0 3 3
21/768		21/90	S 5 F 0 5 8
審査請求 未請求 請求項の数7 OL (全 16 頁)			

(21) 出願番号 特願平11-234603

(22) 出願日 平成11年8月20日 (1999.8.20)

(71) 出願人 000004178

ジェイエスアール株式会社

東京都中央区築地2丁目11番24号

(72) 発明者 西川 通則

東京都中央区築地2丁目11番24号 ジェイ

エスアール株式会社内

(72) 発明者 角田 真由美

東京都中央区築地2丁目11番24号 ジェイ

エスアール株式会社内

(72) 発明者 海老沢 政彦

東京都中央区築地2丁目11番24号 ジェイ

エスアール株式会社内


最終頁に続く

(54) 【発明の名称】 膜形成用組成物および絶縁膜形成用材料

(57) 【要約】


【課題】 半導体素子などにおける層間絶縁膜材料として、塗膜の機械的特性に優れ、短時間で塗膜の焼成が可能であり、非常に低い誘電率を示す膜形成用組成物を得る。

【解決手段】 (A) (A-1) 下記一般式 (1) で



(R³, R⁴, R⁵およびR⁶は、同一でも異なってもよく、それぞれ1価の有機基を示し、bおよびcは、同一でも異なってもよく、0~2の数値を示し、R⁷は酸素原子または-(CH₂)_n-で表される基を示し、nは1~6を、dは0または1を示す。) からなる群より選ばれる少なくとも1種の化合物の加水分解物および縮

表される化合物および



(R¹は水素原子、フッ素原子または1価の有機基を示し、R²は1価の有機基を示し、aは0~2の整数を表す。)

(A-2) 下記一般式 (2) で表される化合物

化合物もしくはいずれか一方

(B) 潜在性酸触媒および潜在性塩基触媒もしくはいずれか一方ならびに

(C) 常圧での沸点が180℃以上の溶剤を含有することを特徴とする膜形成用組成物。

【特許請求の範囲】

【請求項1】 (A) (A-1) 下記一般式(1)で表される化合物および



(R^1 , R^2 , R^3 および R^4 は、同一でも異なっているもよく、それぞれ1価の有機基を示し、 b および c は、同一でも異なっているもよく、0~2の数値を示し、 R^7 は酸素原子または $-(CH_2)_n-$ で表される基を示し、 n は1~6を、 d は0または1を示す。) からなる群より選ばれる少なくとも1種の化合物の加水分解物および縮合物もしくはいずれか一方

(B) 潜在性酸触媒および潜在性塩基触媒もしくはいずれか一方

ならびに

(C) 常圧での沸点が180℃以上の溶剤を含有することを特徴とする膜形成用組成物。

【請求項2】 (D) 常圧での沸点が160℃以下の溶剤をさらに含有することを特徴とする請求項1記載の膜形成用組成物。

【請求項3】 (B) 成分の使用割合が、(A) 成分100重量部(完全加水分解縮合物換算)に対して0.001~10重量部であることを特徴とする請求項1記載の膜形成用組成物。

【請求項4】 (C) 成分が多価アルコール、グリコール系溶剤、グリコールモノアルキルエーテル系溶剤、グリコールジアルキルエーテル系溶剤、グリコールモノアルキルエーテルエステル系溶剤、グリコールジエステル系溶剤から選ばれることを特徴とする請求項1記載の膜形成用組成物。

【請求項5】 組成物中の(C)成分と(D)成分使用割合が、(C):(D)=5:95~50:50(重量比、(C)成分+(D)成分=100)であることを特徴とする請求項1記載の膜形成用組成物。

【請求項6】 さらにβ-ジケトン、ポリアルキレンオキシド構造を有する化合物および(メタ)アクリル系重合体よりなる群から選ばれる少なくとも1種の化合物を含有することを特徴とする請求項1記載の膜形成用組成物。

【請求項7】 請求項1~6記載の膜形成用組成物からなることを特徴とする絶縁膜形成用材料。

【発明の詳細な説明】

【0001】


【発明の属する技術分野】 本発明は、膜形成用組成物に関し、さらに詳しくは、半導体素子などにおける層間絶縁膜材料として、塗膜の機械的特性に優れ、短時間で塗膜の焼成が可能であり、非常に低い誘電率を示す膜形成用組成物に関する。

【0002】

【従来の技術】 従来、半導体素子などにおける層間絶縁

(R^1 は水素原子、フッ素原子または1価の有機基を示し、 R^2 は1価の有機基を示し、 a は0~2の整数を表す。)

(A-2) 下記一般式(2)で表される化合物



膜として、CVD法などの真空プロセスで形成されたシリカ(SiO_2)膜が多用されている。そして、近年、より均一な層間絶縁膜を形成することを目的として、SOG(Spin on Glass)膜と呼ばれるテトラアルコキシランの加水分解生成物を主成分とする塗布型の絶縁膜も使用されるようになってきている。また、半導体素子などの高集積化に伴い、有機SOGと呼ばれるポリオルガノシロキサンを主成分とする低誘電率の層間絶縁膜が開発されている。しかしながら、半導体素子などのさらなる高集積化や多層化に伴い、より優れた導体間の電気絶縁性が要求されており、したがって、より低誘電率で機械的強度に優れた層間絶縁膜材料が求められるようになってきている。

【0003】そこで、特開平6-181201号公報には、層間絶縁膜材料として、より低誘電率の絶縁膜形成用塗布型組成物が開示されている。この塗布型組成物は、吸水性が低く、耐クラック性に優れた半導体装置の絶縁膜を提供することを目的としており、その構成は、チタン、ジルコニウム、ニオブおよびタンタルから選ばれる少なくとも1種の元素を含む有機金属化合物と、分子内にアルコキシ基を少なくとも1個有する有機ケイ素化合物とを縮重合させてなる、数平均分子量が500以上のオリゴマーを主成分とする絶縁膜形成用塗布型組成物である。


【0004】また、WO96/00758号公報には、多層配線基板の層間絶縁膜の形成に使用される、アルコキシシラン類、シラン以外の金属アルコキシドおよび有機溶媒などからなる、厚膜塗布が可能で、かつ耐酸素プラズマ性に優れたシリカ系塗布型絶縁膜形成用材料が開示されている。

【0005】さらに、特開平3-20377号公報には、電子部品などの表面平坦化、層間絶縁などに有用な酸化物被膜形成用塗布液が開示されている。この酸化物被膜形成用塗布液は、ゲル状物の発生のない均一な塗布液を提供し、また、この塗布液を用いることにより、高温での硬化、酸素プラズマによる処理を行った場合であっても、クラックのない良好な酸化物被膜を得ることを目的としている。そして、その構成は、所定のシラン化合物と、同じく所定のキレート化合物とを有機溶媒の存在化で加水分解し、重合して得られる酸化物被膜形成用塗布液である。

【0006】しかし、上記のようにシラン化合物にチタンやジルコニウムなどの金属キレート化合物を組み合わせた場合、塗膜の機械的特性、短時間で塗膜の焼成、非常に低い誘電率などをバランスよく有するものではない。

【0007】

【発明が解決しようとする課題】本発明は、上記問題点を解決するための膜形成用組成物に関し、さらに詳しくは、半導体素子などにおける層間絶縁膜として、塗膜の機械的特性に優れ、短時間で塗膜の焼成が可能であり、非常に低い誘電率を示す層間絶縁膜用材料を提供することを目的とする。



(R^3 , R^4 , R^5 および R^6 は、同一でも異なっているもよく、それぞれ1価の有機基を示し、 b および c は、同一でも異なっているもよく、0~2の数を示し、 R^7 は酸素原子または $-(CH_2)_n-$ で表される基を示し、 n は1~6を、 d は0または1を示す。) から選ばれる少なくとも1種の化合物の加水分解物および縮合物もしくはいずれか一方

(B) 潜在性酸触媒および潜在性塩基触媒もしくはいずれか一方ならびに

(C) 常圧での沸点が180℃以上の溶剤を含有することを特徴とする膜形成用組成物および絶縁膜形成用材料を提供するものである。

【0009】

【発明の実施の形態】

【0010】 (A) 成分

(A-1) 成分

上記一般式(1)において、 R^1 および R^2 の1価の有機基としては、アルキル基、アリール基、アリル基、グリンジル基などを挙げることができる。また、一般式

(1)において、 R^1 は1価の有機基、特にアルキル基またはフェニル基であることが好ましい。ここで、アルキル基としては、メチル基、エチル基、プロピル基、ブチル基などが挙げられ、好ましくは炭素数1~5であり、これらのアルキル基は鎖状でも、分岐していてもよく、さらに酸素原子がフッ素原子などに置換されていてもよい。一般式(1)において、アリール基としては、フェニル基、ナフチル基、メチルフェニル基、エチルフェニル基、クロロフェニル基、プロモフェニル基、フルオロフェニル基などを挙げることができる。

【0011】一般式(1)で表される化合物の具体例としては、トリメトキシシラン、トリエトキシシラン、トリ n -プロポキシシラン、トリ iso -プロポキシシラン、トリ n -ブトキシシラン、トリ sec -ブトキシシラン、トリ $tert$ -ブトキシシラン、トリフェノキシシラン、フルオロトリメトキシシラン、フルオロトリエトキシシラン、フルオロトリ n -プロポキシシラン、フルオロトリ iso -プロポキシシラン、フルオロトリ n -ブトキシシラン、フルオロトリ sec -ブトキシシラン、フルオロトリ $tert$ -ブトキシシラン、フルオロトリフェノキシシラン、テトラメ

【0008】本発明は、

(A) (A-1) 下記一般式(1)で表される化合物
 $R^1_a Si (OR^2)_4 - \dots \dots (1)$

(R^1 は水素原子、フッ素原子または1価の有機基を示し、 R^2 は1価の有機基を示し、 a は0~2の整数を表す。) および (A-2) 下記一般式(2)で表される化合物

トキシシラン、テトラエトキシシラン、テトラ n -プロポキシシラン、テトラ iso -プロポキシシラン、テトラ n -ブトキシシラン、テトラ sec -ブトキシシラン、テトラ $tert$ -ブトキシシラン、テトラフェノキシシランなど；メチルトリメトキシシラン、メチルトリエトキシシラン、メチルトリ n -プロポキシシラン、メチルトリ iso -プロポキシシラン、メチルトリ n -ブトキシシラン、メチルトリ sec -ブトキシシラン、メチルトリ $tert$ -ブトキシシラン、メチルトリフェノキシシラン、エチルトリメトキシシラン、エチルトリエトキシシラン、エチルトリ n -プロポキシシラン、エチルトリ iso -プロポキシシラン、エチルトリ n -ブトキシシラン、エチルトリ sec -ブトキシシラン、エチルトリ $tert$ -ブトキシシラン、エチルトリフェノキシシラン、ビニルトリメトキシシラン、ビニルトリエトキシシラン、ビニルトリ n -プロポキシシラン、ビニルトリ iso -プロポキシシラン、ビニルトリ n -ブトキシシラン、ビニルトリ sec -ブトキシシラン、ビニルトリ $tert$ -ブトキシシラン、ビニルトリフェノキシシラン、 n -プロピルトリメトキシシラン、 n -プロピルトリエトキシシラン、 n -プロピルトリ n -プロポキシシラン、 n -プロピルトリ iso -プロポキシシラン、 n -プロピルトリ n -ブトキシシラン、 n -プロピルトリ sec -ブトキシシラン、 n -プロピルトリ $tert$ -ブトキシシラン、 n -プロピルトリフェノキシシラン、 i -プロピルトリメトキシシラン、 i -プロピルトリエトキシシラン、 i -プロピルトリ n -プロポキシシラン、 i -プロピルトリ iso -プロポキシシラン、 i -プロピルトリ n -ブトキシシラン、 i -プロピルトリ sec -ブトキシシラン、 i -プロピルトリ $tert$ -ブトキシシラン、 i -プロピルトリフェノキシシラン、 n -ブチルトリメトキシシラン、 n -ブチルトリエトキシシラン、 n -ブチルトリ n -プロポキシシラン、 n -ブチルトリ iso -プロポキシシラン、 n -ブチルトリ n -ブトキシシラン、 n -ブチルトリ sec -ブトキシシラン、 n -ブチルトリ $tert$ -ブトキシシラン、 n -ブチルトリフェノキシシラン、 sec -ブチルトリメトキシシラン、 sec -ブチルトリエトキシシラン、 sec -ブチルトリ n -プロポキシシラン、 sec -ブチルトリ iso -

ン、ジ-*n*-ブチル-ジ-*sec*-ブトキシシラン、ジ-*n*-ブチル-ジ-*tert*-ブトキシシラン、ジ-*n*-ブチル-ジ-フェノキシシラン、ジ-*sec*-ブチルジメトキシシラン、ジ-*sec*-ブチルジエトキシシラン、ジ-*sec*-ブチル-ジ-*n*-プロポキシシラン、ジ-*sec*-ブチル-ジ-*iso*-プロポキシシラン、ジ-*sec*-ブチル-ジ-*n*-ブトキシシラン、ジ-*sec*-ブチル-ジ-*sec*-ブトキシシラン、ジ-*sec*-ブチル-ジ-*tert*-ブトキシシラン、ジ-*sec*-ブチル-ジ-フェノキシシラン、ジ-*tert*-ブチルジメトキシシラン、ジ-*tert*-ブチルジエトキシシラン、ジ-*tert*-ブチル-ジ-*n*-プロポキシシラン、ジ-*tert*-ブチル-ジ-*iso*-プロポキシシラン、ジ-*tert*-ブチル-ジ-*n*-ブトキシシラン、ジ-*tert*-ブチル-ジ-*sec*-ブトキシシラン、ジ-*tert*-ブチル-ジ-*tert*-ブトキシシラン、ジ-*tert*-ブチル-ジ-フェノキシシラン、ジフェニルジメトキシシラン、ジフェニル-ジ-エトキシシラン、ジフェニル-ジ-*n*-プロポキシシラン、ジフェニル-ジ-*iso*-プロポキシシラン、ジフェニル-ジ-*n*-ブトキシシラン、ジフェニル-ジ-*sec*-ブトキシシラン、ジフェニル-ジ-*tert*-ブトキシシラン、ジフェニルジフェノキシシラン、ジビニルトリメトキシシラン、γ-アミノプロピルトリメトキシシラン、γ-アミノプロピルトリエトキシシラン、γ-グリシドキシプロピルトリメトキシシラン、γ-グリシドキシプロピルトリエトキシシラン、γ-トリフロプロピルトリメトキシシラン、γ-トリフロプロピルトリエトキシシランなど；を挙げることができる。好ましくは、テトラメトキシシラン、テトラエトキシシラン、テトラ-*n*-プロポキシシラン、テトラ-*iso*-プロポキシシラン、テトラフェノキシシラン、メチルトリメトキシシラン、メチルトリエトキシシラン、メチルトリ-*n*-プロポキシシラン、メチルトリ-*iso*-プロポキシシラン、エチルトリメトキシシラン、エチルトリエトキシシラン、ビニルトリメトキシシラン、ビニルトリエトキシシラン、フェニルトリメトキシシラン、フェニルトリエトキシシラン、ジメチルジメトキシシラン、ジメチルジエトキシシラン、ジエチルジメトキシシラン、ジエチルジエトキシシラン、ジフェニルジメトキシシラン、ジフェニルジエトキシシラン、トリメチルモノメトキシシラン、トリメチルモノエトキシシラン、トリエチルモノメトキシシラン、トリエチルモノエトキシシラン、トリフェニルモノメトキシシラン、トリフェニルモノエトキシシランである。これらは、1種あるいは2種以上を同時に使用してもよい。

上記一般式(2)において、1価の有機基としては、先の一般式(1)と同様な有機基を挙げることができる。また、一般式(2)のR'である2価の有機基として

は、メチレン基、炭素数2～6のアルキレン基などを挙げることができる。一般式(2)のうち、 R^1 が酸素原子の化合物としては、ヘキサメトキシジシロキサン、ヘキサエトキシジシロキサン、ヘキサフェノキシジシロキサン、1, 1, 1, 3, 3-ペンタメトキシ-3-メチルジシロキサン、1, 1, 1, 3, 3-ペンタエトキシ-3-メチルジシロキサン、1, 1, 1, 3, 3-ペンタメトキシ-3-フェニルジシロキサン、1, 1, 1, 3, 3-ペンタエトキシ-3-フェニルジシロキサン、1, 1, 3, 3-テトラメトキシ-1, 3-ジメチルジシロキサン、1, 1, 3, 3-テトラエトキシ-1, 3-ジメチルジシロキサン、1, 1, 3, 3-テトラメトキシ-1, 3-ジフェニルジシロキサン、1, 1, 3, 3-テトラエトキシ-1, 3-ジフェニルジシロキサン、1, 1, 3-トリメトキシ-1, 3, 3-トリメチルジシロキサン、1, 1, 3-トリエトキシ-1, 3, 3-トリメチルジシロキサン、1, 1, 3-トリフェニルジシロキサン、1, 1, 3-トリエトキシ-1, 3, 3-トリフェニルジシロキサン、1, 3-ジメトキシ-1, 1, 3, 3-テトラメチルジシロキサン、1, 3-ジエトキシ-1, 1, 3, 3-テトラメチルジシロキサン、1, 3-ジメトキシ-1, 1, 3, 3-テトラフェニルジシロキサン、1, 3-ジエトキシ-1, 1, 3, 3-テトラフェニルジシロキサンなどを挙げることができる。これらのうち、ヘキサメトキシジシロキサン、ヘキサエトキシジシロキサン、1, 1, 3, 3-テトラメトキシ-1, 3-ジメチルジシロキサン、1, 1, 3, 3-テトラエトキシ-1, 3-ジメチルジシロキサン、1, 1, 3, 3-テトラメトキシ-1, 3-ジフェニルジシロキサン、1, 1, 3, 3-テトラエトキシ-1, 3-ジフェニルジシロキサンなど

を、好ましい例として挙げることができる。一般式(2)においてdが0の化合物としては、ヘキサメトキシジシラン、ヘキサエトキシジシラン、ヘキサフェニキシジシラン、1, 1, 1, 2, 2-ペンタメトキシ-2-メチルジシラン、1, 1, 1, 2, 2-ペンタエトキシ-2-メチルジシラン、1, 1, 1, 2, 2-ペンタメトキシ-2-フェニルジシラン、1, 1, 1, 2, 2-ペンタエトキシ-2-フェニルジシラン、1, 1, 2, 2-テトラメトキシ-1, 2-ジメチルジシラン、1, 1, 2, 2-テトラエトキシ-1, 2-ジメチルジシラン、1, 1, 2, 2-テトラメトキシ-1, 2-ジフェニルジシラン、1, 1, 2, 2-テトラエトキシ-1, 2-ジフェニルジシラン、1, 1, 2-トリメトキシ-1, 2, 2-トリメチルジシラン、1, 1, 2-トリエトキシ-1, 2, 2-トリメチルジシラン、1,

1, 2-トリメトキシ-1, 2, 2-トリフェニルジシラン、1, 1, 2-トリエトキシ-1, 2, 2-トリフェニルジシラン、1, 2-ジメトキシ-1, 1, 2, 2-テトラメチルジシラン、1, 2-ジエトキシ-1, 1, 2, 2-テトラメチルジシラン、1, 2-ジメトキシ-1, 1, 2, 2-テトラフェニルジシラン、1, 2-ジエトキシ-1, 1, 2, 2-テトラフェニルジシランなどを、一般式(2)において R^1 が $-(CH_2)_n-$ で表される基の化合物としては、ビス(ヘキサメトキシシリル)メタン、ビス(ヘキサエトキシシリル)メタン、ビス(ヘキサフェノキシシリル)メタン、ビス(ジメトキシメチルシリル)メタン、ビス(ジエトキシメチルシリル)メタン、ビス(ジメトキシフェニルシリル)メタン、ビス(ジエトキシフェニルシリル)メタン、ビス(メトキシジメチルシリル)メタン、ビス(エトキシジメチルシリル)メタン、ビス(メトキシジフェニルシリル)メタン、ビス(エトキシジフェニルシリル)メタン、ビス(ヘキサメトキシシリル)エタン、ビス(ヘキサエトキシシリル)エタン、ビス(ヘキサフェノキシシリル)エタン、ビス(ジメトキシメチルシリル)エタン、ビス(ジエトキシメチルシリル)エタン、ビス(ジメトキシフェニルシリル)エタン、ビス(ジエトキシフェニルシリル)エタン、ビス(メトキシジメチルシリル)エタン、ビス(エトキシジメチルシリル)エタン、ビス(メトキシジフェニルシリル)エタン、ビス(エトキシジフェニルシリル)エタン、1, 3-ビス(ヘキサメトキシシリル)プロパン、1, 3-ビス(ヘキサエトキシシリル)プロパン、1, 3-ビス(ヘキサフェノキシシリル)プロパン、1, 3-ビス(ジメトキシメチルシリル)プロパン、1, 3-ビス(ジエトキシメチルシリル)プロパン、1, 3-ビス(ジメトキシフェニルシリル)プロパン、1, 3-ビス(ジエトキシフェニルシリル)プロパン、1, 3-ビス(メトキシジメチルシリル)プロパン、1, 3-ビス(エトキシジメチルシリル)プロパン、1, 3-ビス(メトキシジフェニルシリル)プロパン、1, 3-ビス(エトキシジフェニルシリル)プロパンなどを挙げることができる。これらのうち、ヘキサメトキシジシラン、ヘキサエトキシジシラン、ヘキサフェニキシジシラン、1, 1, 2, 2-テトラメトキシ-1, 2-ジメチルジシラン、1, 1, 2, 2-テトラエトキシ-1, 2-ジメチルジシラン、1, 1, 2, 2-テトラメトキシ-1, 2-ジフェニルジシラン、1, 1, 2, 2-テトラエトキシ-1, 2-ジフェニルジシラン、1, 2-ジメトキシ-1, 1, 2, 2-テトラメチルジシラン、1, 2-ジエトキシ-1, 1, 2, 2-テトラメチルジシラン、1, 2-ジメトキシ-1, 1, 2, 2-テトラフェニルジシラン、1, 2-ジエトキシ-1, 1, 2, 2-テトラフェニルジシラン、ビス(ヘキサメトキシシリル)メタン、ビス(ヘキサエトキシシリル)メタン、ビス(ジメトキシメチルシ

リル)メタン、ビス(ジエトキシメチルシリル)メタン、ビス(ジメトキシフェニルシリル)メタン、ビス(ジエトキシフェニルシリル)メタン、ビス(メトキシジメチルシリル)メタン、ビス(エトキシジメチルシリル)メタン、ビス(メトキシジフェニルシリル)メタン、ビス(エトキシジフェニルシリル)メタンを、好ましい例として挙げることができる。本発明において、

(A)成分としては、上記(A-1)成分および(A-2)成分、もしくはいずれか一方を用い、(A-1)成分および(A-2)成分はそれぞれ2種以上用いることもできる。

【0013】本発明において、加水分解とは、上記

(A)成分に含まれる R^2O -基、 R^4O -基、および R^5O -基すべてが加水分解されている必要はなく、例えば1個だけが加水分解されているもの、2個以上が加水分解されているもの、あるいは、これらの混合物が生成することである。本発明において縮合とは(A)成分の加水分解物のシラノール基が縮合してSi-O-Si結合を形成したものであるが、本発明では、シラノール基がすべて縮合している必要はなく、僅かな一部のシラノール基が縮合したもの、縮合の程度が異なっているものの混合物などをも生成することを包含した概念である。なお、(A)成分の加水分解縮合物の重量平均分子量は、通常、1,000~120,000、好ましくは1,200~100,000程度である。

【0014】また、(A)成分を加水分解、部分縮合させる際には、触媒を使用する。この際に使用する触媒としては、金属キレート化合物、有機酸、無機酸、有機塩基、無機塩基を挙げることができる。金属キレート化合物としては、例えばトリエトキシ・モノ(アセチルアセトナート)チタン、トリ-n-プロポキシ・モノ(アセチルアセトナート)チタン、トリ-i-プロポキシ・モノ(アセチルアセトナート)チタン、トリ-n-ブトキシ・モノ(アセチルアセトナート)チタン、トリ-sec-ブトキシ・モノ(アセチルアセトナート)チタン、トリ-tert-ブトキシ・モノ(アセチルアセトナート)チタン、ジエトキシ・ビス(アセチルアセトナート)チタン、ジ-n-プロポキシ・ビス(アセチルアセトナート)チタン、ジ-i-プロポキシ・ビス(アセチルアセトナート)チタン、ジ-n-ブトキシ・ビス(アセチルアセトナート)チタン、ジ-sec-ブトキシ・ビス(アセチルアセトナート)チタン、ジ-tert-ブトキシ・ビス(アセチルアセトナート)チタン、モノエトキシ・トリス(アセチルアセトナート)チタン、モノ-n-プロポキシ・トリス(アセチルアセトナート)チタン、モノ-i-プロポキシ・トリス(アセチルアセトナート)チタン、モノ-n-ブトキシ・トリス(アセチルアセトナート)チタン、モノ-sec-ブトキシ・トリス(アセチルアセトナート)チタン、モノ-tert-ブトキシ・トリス(アセチルアセトナート)チタン、テトラキス(ア

セチルアセトナート)チタン、トリエトキシ・モノ(エチルアセトアセテート)チタン、トリ-n-プロポキシ・モノ(エチルアセトアセテート)チタン、トリ-i-プロポキシ・モノ(エチルアセトアセテート)チタン、トリ-n-ブトキシ・モノ(エチルアセトアセテート)チタン、トリ-sec-ブトキシ・モノ(エチルアセトアセテート)チタン、トリ-tert-ブトキシ・モノ(エチルアセトアセテート)チタン、ジエトキシ・ビス(エチルアセトアセテート)チタン、ジ-n-プロポキシ・ビス(エチルアセトアセテート)チタン、ジ-i-プロポキシ・ビス(エチルアセトアセテート)チタン、ジ-n-ブトキシ・ビス(エチルアセトアセテート)チタン、ジ-sec-ブトキシ・ビス(エチルアセトアセテート)チタン、ジ-tert-ブトキシ・ビス(エチルアセトアセテート)チタン、モノエトキシ・トリス(エチルアセトアセテート)チタン、モノ-n-プロポキシ・トリス(エチルアセトアセテート)チタン、モノ-i-プロポキシ・トリス(エチルアセトアセテート)チタン、モノ-n-ブトキシ・トリス(エチルアセトアセテート)チタン、モノ-sec-ブトキシ・トリス(エチルアセトアセテート)チタン、モノ-tert-ブトキシ・トリス(エチルアセトアセテート)チタン、テトラキス(エチルアセトアセテート)チタン、モノ(アセチルアセトナート)トリス(エチルアセトアセテート)チタン、ビス(アセチルアセトナート)ビス(エチルアセトアセテート)チタン、トリス(アセチルアセトナート)モノ(エチルアセトアセテート)チタン、等のチタンキレート化合物；トリエトキシ・モノ(アセチルアセトナート)ジルコニウム、トリ-n-プロポキシ・モノ(アセチルアセトナート)ジルコニウム、トリ-i-プロポキシ・モノ(アセチルアセトナート)ジルコニウム、トリ-n-ブトキシ・モノ(アセチルアセトナート)ジルコニウム、トリ-sec-ブトキシ・モノ(アセチルアセトナート)ジルコニウム、トリ-tert-ブトキシ・モノ(アセチルアセトナート)ジルコニウム、ジエトキシ・ビス(アセチルアセトナート)ジルコニウム、ジ-n-プロポキシ・ビス(アセチルアセトナート)ジルコニウム、ジ-i-プロポキシ・ビス(アセチルアセトナート)ジルコニウム、ジ-n-ブトキシ・ビス(アセチルアセトナート)ジルコニウム、ジ-sec-ブトキシ・ビス(アセチルアセトナート)ジルコニウム、ジ-tert-ブトキシ・ビス(アセチルアセトナート)ジルコニウム、モノエトキシ・トリス(アセチルアセトナート)ジルコニウム、モノ-n-プロポキシ・トリス(アセチルアセトナート)ジルコニウム、モノ-i-プロポキシ・トリス(アセチルアセトナート)ジルコニウム、モノ-n-ブトキシ・トリス(アセチルアセトナート)ジルコニウム、モノ-sec-ブトキシ・トリス(アセチルアセトナート)ジルコニウム、モノ-tert-ブトキシ・トリス(アセチルアセトナート)ジルコニウム、テトラキス

(アセチルアセトナート) ジルコニウム、トリエトキシ・モノ (エチルアセトアセテート) ジルコニウム、トリ・*n*-プロポキシ・モノ (エチルアセトアセテート) ジルコニウム、トリ・*i*-プロポキシ・モノ (エチルアセトアセテート) ジルコニウム、トリ・*n*-ブトキシ・モノ (エチルアセトアセテート) ジルコニウム、トリ・*s*ec-ブトキシ・モノ (エチルアセトアセテート) ジルコニウム、トリ・*t*-ブトキシ・モノ (エチルアセトアセテート) ジルコニウム、ジエトキシ・ビス (エチルアセトアセテート) ジルコニウム、ジ・*n*-プロポキシ・ビス (エチルアセトアセテート) ジルコニウム、ジ・*i*-プロポキシ・ビス (エチルアセトアセテート) ジルコニウム、ジ・*n*-ブトキシ・ビス (エチルアセトアセテート) ジルコニウム、ジ・*s*ec-ブトキシ・ビス (エチルアセトアセテート) ジルコニウム、ジ・*t*-ブトキシ・ビス (エチルアセトアセテート) ジルコニウム、モノエトキシ・トリス (エチルアセトアセテート) ジルコニウム、モノ・*n*-プロポキシ・トリス (エチルアセトアセテート) ジルコニウム、モノ・*i*-プロポキシ・トリス (エチルアセトアセテート) ジルコニウム、モノ・*n*-ブトキシ・トリス (エチルアセトアセテート) ジルコニウム、モノ・*s*ec-ブトキシ・トリス (エチルアセトアセテート) ジルコニウム、モノ・*t*-ブトキシ・トリス (エチルアセトアセテート) ジルコニウム、テトラキス (エチルアセトアセテート) ジルコニウム、モノ (アセチルアセトナート) トリス (エチルアセトアセテート) ジルコニウム、ビス (アセチルアセトナート) ビス (エチルアセトアセテート) ジルコニウム、トリス (アセチルアセトナート) モノ (エチルアセトアセテート) ジルコニウム、等のジルコニウムキレート化合物; トリス (アセチルアセトナート) アルミニウム、トリス (エチルアセトアセテート) アルミニウム等のアルミニウムキレート化合物; などを挙げる事ができる。有機酸としては、例えば酢酸、プロピオン酸、ブタン酸、ペンタン酸、ヘキサン酸、ヘプタン酸、オクタン酸、ノナン酸、デカン酸、シュウ酸、マレイン酸、メチルマロン酸、アジピン酸、セバシン酸、没食子酸、酪酸、メリット酸、アラキドン酸、ミキミ酸、2-エチルヘキサン酸、オレイン酸、ステアリン酸、リノール酸、リノレイン酸、サリチル酸、安息香酸、*p*-アミノ安息香酸、*p*-トルエンスルホン酸、ベンゼンスルホン酸、モノクロロ酢酸、ジクロロ酢酸、トリクロロ酢酸、トリフルオロ酢酸、ギ酸、マロン酸、スルホン酸、フタル酸、フマル酸、クエン酸、酒石酸等を挙げる事ができる。無機酸としては、例えば塩酸、硝酸、硫酸、フッ酸、リン酸等を挙げる事ができる。有機塩基としては、例えばピリジン、ピロール、ピペラジン、ピロリジン、ピペリジン、ピコリン、トリメチルアミン、トリエチルアミン、モノエタノールアミン、ジエタノールアミン、ジメチルモノエタノールアミン、モノメチルジエタノールアミ

ン、トリエタノールアミン、ジアザビスクロオクラン、ジアザビスクロノナン、ジアザビスクロウンデセン、テトラメチルアンモニウムハイドロオキサイド等を挙げる事ができる。無機塩基としては、例えばアンモニア、水酸化ナトリウム、水酸化カリウム、水酸化バリウム、水酸化カルシウム等を挙げる事ができる。これら触媒の内、金属キレート化合物、有機酸、無機酸が好ましく、より好ましくはチタンキレート化合物、有機酸を挙げる事ができる。これらは1種あるいは2種以上を同時に使用しても良い。

【0015】上記触媒の使用量は(A)成分(完全加水分解縮合物換算)のそれぞれ100重量部に対して、通常、0.001~10重量部、好ましくは0.01~10重量部の範囲である。また、触媒は、前記溶剤中に予め添加しておいてもよいし、水添加時に水中に溶解あるいは分散させておいてもよい。

【0016】(B)成分

本発明の膜形成用組成物は、潜在性酸触媒および潜在性塩基触媒もしくはいずれか一方を含有する。潜在性酸触媒としては、例えば熱酸発生剤および光酸発生剤などを挙げる事ができる。熱酸発生剤は、通常50~450℃、好ましくは200~350℃に加熱することにより酸を発生する化合物であり、スルホニウム塩、ベンゾチアゾリウム塩、アンモニウム塩、ホスホニウム塩などのオニウム塩が用いられる。

【0017】上記スルホニウム塩の具体例としては、4-アセトフェニルジメチルスルホニウム ヘキサフルオロアンチモネート、4-アセトキシフェニルジメチルスルホニウム ヘキサフルオロアルセネート、ジメチル-4-(ベンジルオキシカルボニルオキシ)フェニルスルホニウム ヘキサフルオロアンチモネート、ジメチル-4-(ベンゾイルオキシ)フェニルスルホニウム ヘキサフルオロアンチモネート、ジメチル-4-(ベンゾイルオキシ)フェニルスルホニウム ヘキサフルオロアルセネート、ジメチル-3-クロロ-4-アセトキシフェニルスルホニウム ヘキサフルオロアンチモネートなどのアルキルスルホニウム塩; ベンジル-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロアンチモネート、ベンジル-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロホスフェート、4-アセトキシフェニルベンジルメチルスルホニウム ヘキサフルオロアンチモネート、ベンジル-4-メトキシフェニルメチルスルホニウム ヘキサフルオロアンチモネート、ベンジル-2-メチル-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロアンチモネート、ベンジル-3-クロロ-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロアルセネート、4-メトキシベンジル-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロホスフェート、ベンゾイントシレート、2-ニトロベンジルトシレート、などのベンジルスルホニ

ウム塩；

【0018】ジベンジル-4-ヒドロキシフェニルスルホニウム ヘキサフルオロアンチモネート、ジベンジル-4-ヒドロキシフェニルスルホニウム ヘキサフルオロホスフェート、4-アセトキシフェニルジベンジルスルホニウム ヘキサフルオロアンチモネート、ジベンジル-4-メトキシフェニルスルホニウム ヘキサフルオロアンチモネート、ジベンジル-3-クロロ-4-ヒドロキシフェニルスルホニウム ヘキサフルオロアルセネート、ジベンジル-3-メチル-4-ヒドロキシ-5-tert-ブチルフェニルスルホニウム ヘキサフルオロアンチモネート、ベンジル-4-メトキシベンジル-4-ヒドロキシフェニルスルホニウム ヘキサフルオロホスフェートなどのジベンジルスルホニウム塩；p-クロロベンジル-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロアンチモネート、p-ニトロベンジル-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロホスフェート、p-ニトロベンジル-3-メチル-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロアンチモネート、3,5-ジクロロベンジル-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロアンチモネート、o-クロロベンジル-3-クロロ-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロアンチモネートなどの置換ベンジルスルホニウム塩；

【0019】上記ベンゾチアゾニウム塩の具体例としては3-ベンジルベンゾチアゾリウムヘキサフルオロアンチモネート、3-ベンジルベンゾチアゾリウム ヘキサフルオロホスフェート、3-ベンジルベンゾチアゾリウム テトラフルオロボレート、3-(p-メトキシベンジル)ベンゾチアゾリウム ヘキサフルオロアンチモネート、3-ベンジル-2-メチルチオベンゾチアゾリウム ヘキサフルオロアンチモネート、3-ベンジル-5-クロロベンゾチアゾリウム ヘキサフルオロアンチモネートなどのベンジルベンゾチアゾリウム塩が挙げられる。さらに、上記以外の熱酸発生剤として、2, 4, 4, 6-テトラブロモシクロヘキサジエノンを例示できる。

【0020】これらのうち、4-アセトキシフェニルジメチルスルホニウム ヘキサフルオロアルセネート、ベンジル-4-ヒドロキシフェニルメチルスルホニウム ヘキサフルオロアンチモネート、4-アセトキシフェニルベンジルメチルスルホニウム ヘキサフルオロアンチモネート、ジベンジル-4-ヒドロキシフェニルスルホニウム ヘキサフルオロアンチモネート、4-アセトキシフェニルベンジルスルホニウム ヘキサフルオロアンチモネート、3-ベンジルベンゾチアゾリウムヘキサフルオロアンチモネートなどが好ましく用いられる。これ

らの市販品としては、サンエイド SI-L85、同SI-L110、同SI-L145、同SI-L150、同SI-L160（三新化学工業（株）製）などが挙げられる。これらの化合物は、単独であるいは2種以上組み合わせで用いることができる。

【0021】本発明で用いられる潜在性光酸発生剤は、通常1~100mJ、好ましくは10~50mJの紫外光照射により酸を発生する化合物である。光酸発生剤としては、例えばジフェニルヨードニウムトリフルオロメタンスルホネート、ジフェニルヨードニウムピレンスルホネート、ジフェニルヨードニウムドデシルベンゼンスルホネート、ジフェニルヨードニウムノナフルオロn-ブタンスルホネート、ビス（4-tert-ブチルフェニル）ヨードニウムトリフルオロメタンスルホネート、ビス（4-tert-ブチルフェニル）ヨードニウムドデシルベンゼンスルホネート、ビス（4-tert-ブチルフェニル）ヨードニウムナフタレンスルホネート、ビス（4-tert-ブチルフェニル）ヨードニウムヘキサフルオロアンチモネート、ビス（4-tert-ブチルフェニル）ヨードニウムノナフルオロn-ブタンスルホネート、トリフェニルスルホニウムトリフルオロメタンスルホネート、トリフェニルスルホニウムヘキサフルオロアンチモネート、トリフェニルスルホニウムナフタレンスルホネート、トリフェニルスルホニウムノナフルオロn-ブタンスルホネート、ジフェニル（4-メチルフェニル）スルホニウムトリフルオロメタンスルホネート、ジフェニル（4-メトキシフェニル）スルホニウムトリフルオロメタンスルホネート、（ヒドロキシフェニル）ベンゼンメチルスルホニウムトルエンスルホネート、シクロヘキシルメチル（2-オキシシクロヘキシル）スルホニウムトリフルオロメタンスルホネート、ジシクロヘキシル（2-オキシシクロヘキシル）スルホニウムトリフルオロメタンスルホネート、ジメチル（2-オキシシクロヘキシル）スルホニウムトリフルオロメタンスルホネート、ジフェニルヨードニウムヘキサフルオロアンチモネート、トリフェニルスルホニウムカンファースルホネート、（4-ヒドロキシフェニル）ベンジルメチルスルホニウムトルエンスルホネート、1-ナフチルジメチルスルホニウムトリフルオロメタンスルホネート、1-ナフチルジエチルスルホニウムトリフルオロメタンスルホネート、4-シアノー1-ナフチルジメチルスルホニウムトリフルオロメタンスルホネート、4-ニトロ1-ナフチルジメチルスルホニウムトリフルオロメタンスルホネート、4-メチル1-ナフチルジメチルスルホニウムトリフルオロメタンスルホネート、4-シアノー1-ナフチルジエチルスルホニウムトリフルオロメタンスルホネート、4-ニトロ1-ナフチルジエチルスルホニウムトリフルオロメタンスルホネート、4-メチル1-ナフチルジエチルスルホニウムトリフルオロメタンスルホネート、4-ヒドロキシ1-ナフチルジメチルスルホニウムト

リフルオロメタンスルホネート、4-ヒドロキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-メトキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-エトキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-メトキシメトキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-エトキシメトキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-(1-メトキシエトキシ)-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-(2-メトキシエトキシ)-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-メトキシカルボニルオキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-エトキシカルボニルオキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-n-プロポキシカルボニルオキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-i-プロポキシカルボニルオキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-n-ブトキシカルボニルオキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-t-ブトキシカルボニルオキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-(2-テトラヒドロフランオキシ)-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-(2-テトラヒドロピランオキシ)-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、4-ベンジルオキシ-1-ナフチルテトラヒドロチオフェニウムトリフルオロメタンスルホネート、1-(ナフチルアセトメチル)テトラヒドロチオフェニウムトリフルオロメタンスルホネート等のオニウム塩系光酸発生剤類；フェニル-ビス(トリクロロメチル)-s-トリアジン、メトキシフェニル-ビス(トリクロロメチル)-s-トリアジン、ナフチル-ビス(トリクロロメチル)-s-トリアジン等のハロゲン含有化合物系光酸発生剤類；1,2-ナフトキノンジアジド-4-スルホニルクロリド、1,2-ナフトキノンジアジド-5-スルホニルクロリド、2,3,4,4'-テトラベンゾフェノンの1,2-ナフトキノンジアジド-4-スルホン酸エステルまたは1,2-ナフトキノンジアジド-5-スルホン酸エステル等のジアゾケトン化合物系光酸発生剤類；4-トリスフェナシルスルホン、メシチルフェナシルスルホン、ビス(フェニルスルホニル)メタン等のスルホン酸化合物系光酸発生剤類；ベンゾイントシレート、ピロガロールのトリストリフルオロメタンスルホネート、ニトロベンジル-9,10-ジオキシアントラセン-2-スルホネート、トリフルオロメタンスルホニ

ルビシクロ[2,2,1]ヘプト-5-エン-2,3-ジカルボジイミド、N-ヒドロキシスクシンイミドトリフルオロメタンスルホネート、1,8-ナフタレンジカルボン酸イミドトリフルオロメタンスルホネート等のスルホン酸化合物系光酸発生剤類等が挙げられる。これらの化合物は、単独であるいは2種以上組み合わせて用いることができる。

【0022】また前記潜在性塩基触媒とは外部の刺激により塩基を発生することができるが、外部刺激としては紫外線や熱が好ましく、オルトニトロベンジルカルバメート類、 α 、 α -ジメチル-3,5-ジメトキシベンジルカルバメート類、アシルオキシイミノ類などを例示することができる。また、光により発生する塩基としてはヒドラジン、テトラメチレンジアミン、トルエンジアミン、ジアミノジフェニルメタン、ヘキサメチルテトラアミン、アンモニア、メチルアミン、エチルアミン、プロピルアミン、ブチルアミン、ヘキシルアミン、シクロヘキシルアミン、デシルアミン、セチルアミン、ピペリジン、ピペラジンなどが挙げられる。さらに具体的には

10 [[(2-ニトロベンジル) オキシ] カルボニル] メチルアミン、[[(2-ニトロベンジル) オキシ] カルボニル] プロピルアミン、[[(2-ニトロベンジル) オキシ] カルボニル] ヘキシルアミン、[[(2-ニトロベンジル) オキシ] カルボニル] シクロヘキシルアミン、[[(2-ニトロベンジル) オキシ] カルボニル] アニリン、[[(2-ニトロベンジル) オキシ] カルボニル] ピペリジン、[[(2-ニトロベンジル) オキシ] カルボニル] ヘキサメチレンジアミン、[[(2-ニトロベンジル) オキシ] カルボニル] フェニレンジアミン、[[(2-ニトロベンジル) オキシ] カルボニル] トルエンジアミン、[[(2-ニトロベンジル) オキシ] カルボニル] ジアミノジフェニルメタン、[[(2-ニトロベンジル) オキシ] カルボニル] ピペラジン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] メチルアミン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] プロピルアミン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] ヘキシルアミン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] シクロヘキシルアミン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] アニリン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] ピペリジン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] ヘキサメチレンジアミン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] フェニレンジアミン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] トルエンジアミン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] ジアミノジフェニルメタン、[[(2,6-ジニトロベンジル) オキシ] カルボニル] ピペラジン、[[(α 、 α -ジメチル-3,5-ジメトキシベンジ

ル) オキシ] カルボニルメチルアミン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルプロピルアミン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルヘキシルアミン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルシクロヘキシルアミン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルアニリン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルピペリジン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルヘキサメチレンジアミン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルフェニレンジアミン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルトルエンジアミン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルジアミノジフェニルメタン、[[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルピペラジン、プロピオニルアセトフェノンオキシム、プロピオニルベンゾフェノンオキシム、プロピオニルアセトンオキシム、ブチリルアセトフェノンオキシム、ブチリルベンゾフェノンオキシム、ブチリルアセトンオキシム、アジポイルアセトフェノンオキシム、アジポイルベンゾフェノンオキシム、アジポイルアセトンオキシム、アクロイルアセトフェノンオキシム、アクロイルベンゾフェノンオキシム、アクロイルアセトンオキシムなどが挙げられる。中でも [[(2-ニトロベンジル) オキシ] カルボニル] シクロヘキシルアミン、[[(2-ニトロベンジル) オキシ] カルボニル] ヘキサメチレンジアミン、[(α、α-ジメチル-3, 5-ジメトキシベンジル) オキシ] カルボニルヘキサメチレンジアミンが挙げられる。これらの化合物は、単独であるいは2種以上組み合わせる用いることができる。

【0023】本発明組成物中の (B) 成分の使用割合は、(A) 成分100重量部 (完全加水分解縮合物換算) に対して0.001~10重量部であり、より好ましくは0.01~10重量部である。(B) 成分の使用量が0.001重量部未満であると塗膜の誘電率が十分低い値とならず、(B) 成分の使用量が10重量部を越えると溶液の保存安定性が劣化する場合がある。

【0024】(C) 成分

本発明に使用する (C) 成分は、常圧での沸点が180℃以上の溶剤であり、多価アルコール、グリコール系溶剤、グリコールモノアルキルエーテル系溶剤、グリコールジアルキルエーテル系溶剤、グリコールモノアルキルエーテルエステル系溶剤、グリコールジエステル系溶剤などを挙げることができる。これら溶剤の具体例としては、例えばエチレングリコール、1, 3-プロパンジオール、1, 2-プロパンジオール、1, 4-ブタンジオール、1, 3-ブタンジオール、1, 2-ブタンジオール、

1, 5-ペンタンジオール、1, 4-ペンタンジオール、1, 3-ペンタンジオール、1, 2-ペンタンジオール、1, 6-ヘキサジオール、1, 5-ヘキサジオール、1, 4-ヘキサジオール、1, 3-ヘキサジオール、1, 2-ヘキサジオール、1, 7-ヘプタンジオール、1, 2-ヘプタンジオール、1, 8-オクタジオール、1, 2-オクタジオール、1, 9-ノナンジオール、1, 2-ノナンジオール、1, 10-デカンジオール、1, 2-デカンジオール、1, 12-ドデカンジオール、1, 2-ドデカンジオール、1, 14-テトラデカンジオール、1, 2-テトラデカンジオール、1, 16-ヘキサデカンジオール、1, 2-ヘキサデカンジオール、1, 18-オクタデカンジオール、1, 2-オクタデカンジオール、シクロヘキサジオール、アダマンタンジオール、ジシクロペンタンジオール、グリセリン、ネオペンチルグリコール、トリメチロールプロパン、ペンタエリスリトール、ジグリセリン、ソルビトールなどの多価アルコール；ジエチレングリコール、ジプロピレングリコール、トリエチレングリコール、トリプロピレングリコール、テトラエチレングリコール、テトラプロピレングリコール、ペンタエチレングリコール、ペンタプロピレングリコールなどのグリコール溶剤；ジエチレングリコールモノメチルエーテル、ジエチレングリコールモノエチルエーテル、ジエチレングリコールモノプロピルエーテル、ジエチレングリコールモノブチルエーテル、ジプロピレングリコールモノメチルエーテル、ジプロピレングリコールモノエチルエーテル、ジプロピレングリコールモノプロピルエーテル、ジプロピレングリコールモノブチルエーテル、トリエチレングリコールモノメチルエーテル、トリエチレングリコールモノエチルエーテル、トリエチレングリコールモノプロピルエーテル、トリエチレングリコールモノブチルエーテル、トリプロピレングリコールモノメチルエーテル、トリプロピレングリコールモノエチルエーテル、トリプロピレングリコールモノプロピルエーテル、トリプロピレングリコールモノブチルエーテル、テトラエチレングリコールモノメチルエーテル、テトラエチレングリコールモノエチルエーテル、テトラエチレングリコールモノプロピルエーテル、テトラエチレングリコールモノブチルエーテル、テトラプロピレングリコールモノメチルエーテル、テトラプロピレングリコールモノエチルエーテル、テトラプロピレングリコールモノプロピルエーテル、テトラプロピレングリコールモノブチルエーテルなどのグリコールモノアルキルエーテル系溶剤；ジエチレングリコールジエチルエーテル、ジエチレングリコールジプロピルエーテル、ジエチレングリコールジブチルエーテル、ジプロピレングリコールジエチルエーテル、ジプロピレングリコールジプロピルエーテル、ジプロピレングリコールジブチルエーテル、トリエチレングリコールジメチルエーテル、トリエチレングリコールジエチ

ルエーテル、トリエチレングリコールジプロピルエーテル、トリエチレングリコールジブチルエーテル、トリプロピレングリコールジメチルエーテル、トリプロピレングリコールジエチルエーテル、トリプロピレングリコールジプロピルエーテル、トリプロピレングリコールジブチルエーテル、テトラエチレングリコールジメチルエーテル、テトラエチレングリコールジエチルエーテル、テトラエチレングリコールジプロピルエーテル、テトラエチレングリコールジブチルエーテル、テトラプロピレングリコールジメチルエーテル、テトラプロピレングリコールジエチルエーテル、テトラプロピレングリコールジプロピルエーテル、テトラプロピレングリコールジブチルエーテルなどのグリコールジアシルエーテル系溶剤；ジエチレングリコールモノメチルエーテルアセテート、ジエチレングリコールモノエチルエーテルアセテート、ジエチレングリコールモノプロピルエーテルアセテート、ジエチレングリコールモノブチルエーテルアセテート、ジプロピレングリコールモノメチルエーテルアセテート、ジプロピレングリコールモノエチルエーテルアセテート、ジプロピレングリコールモノプロピルエーテルアセテート、ジプロピレングリコールモノブチルエーテルアセテート、トリエチレングリコールモノメチルエーテルアセテート、トリエチレングリコールモノエチルエーテルアセテート、トリエチレングリコールモノプロピルエーテルアセテート、トリエチレングリコールモノブチルエーテルアセテート、トリプロピレングリコールモノメチルエーテルアセテート、トリプロピレングリコールモノエチルエーテルアセテート、トリプロピレングリコールモノプロピルエーテルアセテート、トリプロピレングリコールモノブチルエーテルアセテート、テトラエチレングリコールモノメチルエーテルアセテート、テトラエチレングリコールモノエチルエーテルアセテート、テトラエチレングリコールモノプロピルエーテルアセテート、テトラエチレングリコールモノブチルエーテルアセテート、テトラプロピレングリコールモノメチルエーテルアセテート、テトラプロピレングリコールモノエチルエーテルアセテート、テトラプロピレングリコールモノプロピルエーテルアセテート、テトラプロピレングリコールモノブチルエーテルアセテートなどのグリコールモノアルキルエーテルエステル系溶剤；エチレングリコールジアセテート、プロピレングリコールジアセテート、ジエチレングリコールジアセテート、ジプロピレングリコールジアセテート、トリエチレングリコールジアセテート、トリプロピレングリコールジアセテート、テトラエチレングリコールジアセテート、テトラプロピレングリコールジアセテートなどのグリコールジエステル系溶剤を挙げることができる。これらの中で、エチレングリコール、1, 3-プロパンジオール、1, 2-プロパンジオール、1, 4-ブタンジオール、グリセリン、ネオペンチルグリコール、トリメチロールプロパ

ン、ペンタエリスリトール、ジグリセリン、ソルビトール、ジエチレングリコール、ジプロピレングリコール、トリエチレングリコール、トリプロピレングリコール、ジエチレングリコールモノメチルエーテル、ジエチレングリコールモノエチルエーテル、ジエチレングリコールモノプロピルエーテル、ジエチレングリコールモノブチルエーテル、ジプロピレングリコールモノメチルエーテル、ジプロピレングリコールモノエチルエーテル、ジプロピレングリコールモノプロピルエーテル、ジプロピレングリコールモノブチルエーテル、トリエチレングリコールモノメチルエーテル、トリエチレングリコールモノエチルエーテル、トリエチレングリコールモノプロピルエーテル、トリエチレングリコールモノブチルエーテル、トリプロピレングリコールモノメチルエーテル、トリプロピレングリコールモノエチルエーテル、トリプロピレングリコールモノプロピルエーテル、トリプロピレングリコールモノブチルエーテル、ジエチレングリコールモノメチルエーテルアセテート、ジエチレングリコールモノエチルエーテルアセテート、ジエチレングリコールモノプロピルエーテルアセテート、ジエチレングリコールモノブチルエーテルアセテート、ジプロピレングリコールモノメチルエーテルアセテート、ジプロピレングリコールモノエチルエーテルアセテート、ジプロピレングリコールモノプロピルエーテルアセテート、ジプロピレングリコールモノブチルエーテルアセテート、トリエチレングリコールモノメチルエーテルアセテート、トリエチレングリコールモノエチルエーテルアセテート、トリエチレングリコールモノプロピルエーテルアセテート、トリエチレングリコールモノブチルエーテルアセテート、トリエチレングリコールモノメチルエーテルアセテート、トリエチレングリコールモノエチルエーテルアセテート、トリエチレングリコールモノプロピルエーテルアセテート、トリエチレングリコールモノブチルエーテルアセテート、トリプロピレングリコールモノメチルエーテルアセテート、トリプロピレングリコールモノエチルエーテルアセテート、トリプロピレングリコールモノプロピルエーテルアセテート、トリプロピレングリコールモノブチルエーテルアセテート、エチレングリコールジアセテート、プロピレングリコールジアセテート、ジエチレングリコールジアセテート、ジプロピレングリコールジアセテート、トリエチレングリコールジアセテート、トリプロピレングリコールジアセテートを特に好ましい例として挙げることができる。これらは1種または2種以上を同時に使用することができる。

【0025】(D) 成分

本発明に使用する(D)成分は、常圧での沸点が160℃以下の溶剤であり、例えばn-ペンタン、i-ペンタン、n-ヘキサン、i-ヘキサン、n-ヘプタン、i-ヘプタン、2, 2, 4-トリメチルペンタン、n-オクタン、i-オクタン、シクロヘキサン、メチルシクロヘキサン等の脂肪族炭化水素系溶媒；ベンゼン、トルエン、キシレン、エチルベンゼン等の芳香族炭化水素系溶媒；メタノール、エタノール、n-プロパノール、i-プロパノール、n-ブタノール、i-ブタノール、se

c-ブタノール、t-ブタノール、n-ペンタノール、i-ペンタノール、2-メチルブタノール、sec-ペンタノール、t-ペンタノール、3-メトキシブタノール、n-ヘキサノール等のモノアルコール系溶媒；アセトン、メチルエチルケトン、メチル-n-プロピルケトン、メチル-n-ブチルケトン、ジエチルケトン、メチル-i-ブチルケトン、メチル-n-ペンチルケトン、エチル-n-ブチルケトン、メチル-n-ヘキシルケトン、ジ-i-ブチルケトン、トリメチルノナノン、シクロヘキサノン、メチルシクロヘキサノン、2, 4-ペンタンジオン等のケトン系溶媒；エチルエーテル、i-プロピルエーテル、n-ブチルエーテル、n-ヘキシルエーテル、2-エチルヘキシルエーテル、エチレンオキシド、1, 2-プロピレンオキシド、ジオキソラン、4-メチルジオキソラン、ジオキサン、ジメチルジオキサン、エチレングリコールモノメチルエーテル、エチレングリコールモノエチルエーテル、エチレングリコールジエチルエーテル、プロピレングリコールモノメチルエーテル、プロピレングリコールモノエチルエーテル、プロピレングリコールモノプロピルエーテル、テトラヒドロフラン、2-メチルテトラヒドロフラン等のエーテル系溶媒；酢酸メチル、酢酸エチル、酢酸-n-プロピル、酢酸-i-プロピル、酢酸-n-ブチル、酢酸-i-ブチル、酢酸-sec-ブチル、酢酸-n-ペンチル、酢酸-sec-ペンチル、酢酸-3-メトキシブチル、酢酸メチルペンチル、酢酸-2-エチルブチル、アセト酢酸メチル、アセト酢酸エチル、酢酸エチレングリコールモノメチルエーテル、酢酸エチレングリコールモノエチルエーテル、酢酸プロピレングリコールモノメチルエーテル、酢酸プロピレングリコールモノエチルエーテル、酢酸プロピオン酸エチル、プロピオン酸-n-ブチル、プロピオン酸-i-アミル、シュウ酸ジエチル、シュウ酸ジ-n-ブチル、乳酸メチル、乳酸エチル、マロン酸ジエチル、3-メトキシメチルプロピオネート、3-エトキシエチルプロピオネート等のエステル系溶媒；N-メチルホルムアミド、N, N-ジメチルホルムアミド、等の含窒素系溶媒を挙げることができる。これらの中で、メタノール、エタノール、n-プロパノール、i-プロパノール、n-ブタノール、i-ブタノール、sec-ブタノール、t-ブタノール、メチルエチルケトン、メチル-n-プロピルケトン、メチル-n-ブチルケトン、ジエチルケトン、メチル-i-ブチルケトン、メチル-n-ペンチルケトン、エチル-n-ブチルケトン、メチル-n-ヘキシルケトン、ジ-i-ブチルケトン、シクロヘキサノン、メチルシクロヘキサノン、2, 4-ペンタンジオン、エチレングリコールモノメチルエーテル、エチレングリコールモノエチルエーテル、エチレングリコールジエチルエーテル、プロピレングリコールモノメチルエーテル、プロピレングリコールモノエチルエーテル、プロピレングリコールモノプロピルエーテ

ル、酢酸エチル、酢酸-n-プロピル、酢酸-i-プロピル、酢酸-n-ブチル、酢酸-i-ブチル、酢酸-sec-ブチル、酢酸-3-メトキシブチル、酢酸メチルペンチル、酢酸-2-エチルブチル、アセト酢酸メチル、アセト酢酸エチル、酢酸エチレングリコールモノメチルエーテル、酢酸エチレングリコールモノエチルエーテル、酢酸プロピレングリコールモノメチルエーテル、酢酸プロピレングリコールモノエチルエーテル、酢酸プロピオン酸-n-ブチル、プロピオン酸-i-アミル、シュウ酸ジエチル、シュウ酸ジ-n-ブチル、乳酸メチル、乳酸エチル、マロン酸ジエチル、3-メトキシメチルプロピオネート、3-エトキシエチルプロピオネートを特に好ましい例として挙げることができる。これらは1種あるいは2種以上を混合して使用することができる。

【0026】組成物中の(C)成分と(D)成分使用割合は、(C) : (D) = 5 : 95 ~ 50 : 50 (重量比)であり、より好ましくは(C) : (D) = 8 : 92 ~ 45 : 55 (重量比)である。(C)成分量が5%未満であると塗膜の錆電率が十分低い値とならず、(C)成分量が50%を越えると溶液の塗布性が劣化する場合がある。

【0027】(A)成分を加水分解する際には、上記の(C)成分および(D)成分もしくはいずれか一方の有機溶媒中で行うことができ、得られた溶液に更に(C)成分および(D)成分もしくはいずれか一方を添加しても良い。

【0028】本発明において、膜形成用組成物中の沸点100℃以下のアルコールの含量が、20重量%以下、特に5重量%以下であることが好ましい。沸点100℃以下のアルコールは、上記(A-1)成分ならびに(A-2)成分の加水分解および縮合の際に生じる場合があり、その含量が20重量%以下、好ましくは5重量%以下になるように蒸留などにより除去することが好ましい。

【0029】本発明の膜形成用組成物は、さらに下記のような成分を含有してもよい。

β-ジケトン

β-ジケトンとしては、アセチルアセトン、2, 4-ヘキサジオン、2, 4-ヘプタンジオン、3, 5-ヘプタンジオン、2, 4-オクタンジオン、3, 5-オクタンジオン、2, 4-ノナンジオン、3, 5-ノナンジオン、5-メチル-2, 4-ヘキサジオン、2, 2, 6, 6-テトラメチル-3, 5-ヘプタンジオン、1, 1, 1, 5, 5, 5-ヘキサフルオロ-2, 4-ヘプタンジオンなどの1種または2種以上である。本発明において、膜形成用組成物中のβ-ジケトン含有量は、

(A)成分(完全加水分解縮合物換算)の合計量100重量部に対して通常0.1~100重量部、好ましくは0.2~80重量部の範囲である。このような範囲でβ

ージケトンを添加すれば、一定の保存安定性が得られるとともに、膜形成用組成物の塗膜均一性などの特性が低下するおそれが少ない。このβ-ジケトンは、(A)成分の加水分解、縮合反応後に添加することが好ましい。

【0030】その他の添加剤

本発明で得られる膜形成用組成物には、さらにコロイド状シリカ、コロイド状アルミナ、有機ポリマー、界面活性剤などの成分を添加してもよい。コロイド状シリカとは、例えば、高純度の無水ケイ酸を前記親水性有機溶媒に分散した分散液であり、通常、平均粒径が5~30μm、好ましくは10~20μm、固形分濃度が10~40重量%程度のものである。このような、コロイド状シリカとしては、例えば、日産化学工業(株)製のメタノールシリカゾルおよびイソプロパノールシリカゾル；触媒化成工業(株)製のオスカルなどが挙げられる。コロイド状アルミナとしては、日産化学工業(株)製のアルミナゾル520、同100、同200；川研ファインケミカル(株)製のアルミナクリアゾル、アルミナゾル10、同132などが挙げられる。有機ポリマーとしては、例えば、ポリアルキレンオキサイド構造を有する化合物、糖鎖構造を有する化合物、ビニルアミド系重合体、(メタ)アクリル系重合体、芳香族ビニル化合物、デンドリマー、ポリイミド、ポリアミック酸、ポリアリーレン、ポリアミド、ポリキノキサリン、ポリオキサジアゾール、フッ素系重合体などを挙げることができる。界面活性剤としては、例えばノニオン系界面活性剤、アニオン系界面活性剤、カチオン系界面活性剤、両性界面活性剤などが挙げられ、さらに、シリコーン系界面活性剤、ポリアルキレンオキシド系界面活性剤、含フッ素界面活性剤、アクリル系界面活性剤等を挙げることができる。前記ノニオン系界面活性剤の具体例としては、ポリオキシエチレンラウリルエーテル、ポリオキシエチレンステアarylエーテル、ポリオキシエチレンオレイルエーテル等のポリオキシエチレンアルキルエーテル類；ポリオキシエチレンn-オクチルフェニルエーテル、ポリオキシエチレンn-ニルフェニルエーテル等のポリオキシエチレンアルキルフェニルエーテル類；ポリエチレングリコールジラウレート、ポリエチレングリコールジステアレート等のポリエチレングリコールジエステル類などを挙げることができる。前記フッ素系界面活性剤の具体例としては、末端、主鎖および側鎖の少なくとも何れかの部位にフルオロアルキルまたはフルオロアルキレン基を有する化合物を好適に用いることができる。その具体例としては、1,1,2,2-テトラフロロオクチル(1,1,2,2-テトラフロロプロピル)エーテル、1,1,2,2-テトラフロロオクチルヘキシルエーテル、オクタエチレングリコールジ(1,1,2,2-テトラフロロプロピル)エーテル、ヘキサエチレングリコール(1,1,2,2,3,3-ヘキサフロロベンチル)エーテル、オクタプロピレングリコールジ(1,1,2,2-テトラ

ロプロピル)エーテル、ヘキサプロピレングリコールジ(1,1,2,2,3,3-ヘキサフロロベンチル)エーテル、パーフロロデシルスルホン酸ナトリウム、1,1,2,2,8,8,9,9,10,10-デカフロロデカン、1,1,2,2,3,3-ヘキサフロロデカン、フルオロアルキルベンゼンスルホン酸ナトリウム、フルオロアルキルオキシエチレンエーテル、ジグリセリントラキスフルオロアルキルアンモニウムヨージド、フルオロアルキルポリオキシエチレンエーテル、パーフルオロアルキルポリオキシエタノール、パーフルオロアルキルアルコキシレート、フッ素系アルキルエステル等を挙げることができる。また、これらの市販品としては、BM-100、BM-1100(以上、BM Chemie社製)、メガファックF142D、同F172、同F173、同F183、同F178、同F191、同F471、(以上、大日本インキ化学工業(株)製)、フロワードFC-170C、FC-171、FC-430、FC-431(以上、住友スリーエム(株))等を挙げることができる。前記シリコーン系界面活性剤の具体例としては、例えばトーレスシリコーンDC3PA、同DC7PA、同SH11PA、同SH21PA、同SH28PA、同SH29PA、同SH30PA(以上、トーレスシリコーン(株)製)、TSF-4440、TSF-4300、TSF-4445、TSF-4446、TSF-4460、TSF-4452(以上、東芝シリコーン(株)製)等の商品名で市販されているものを挙げることができる。その他の界面活性剤としては、例えばソルビタン脂肪酸エステル類；脂肪酸変性ポリエステル類；3級アミン変性ポリウレタン類；ポリエチレンイミン類などを挙げることができる。これらの界面活性剤は単独または2種以上を組み合わせて使用することができる。

【0031】本発明の膜形成用組成物の全固形分濃度は、好ましくは、2~30重量%であり、使用目的に応じて適宜調整される。組成物の全固形分濃度が2~30重量%であると、塗膜の膜厚が適当な範囲となり、保存安定性もより優れるものである。

【0032】本発明の組成物を、シリコンウエハ、SiO₂ウエハ、SiNウエハなどの基材に塗布する際には、スピンコート、浸漬法、ロールコート法、スプレー法などの塗装手段が用いられる。

【0033】この際の膜厚は、乾燥膜厚として、1回塗りでは厚さ0.05~1.5μm程度、2回塗りでは厚さ0.1~3μm程度の塗膜を形成することができる。その後、常温で乾燥するか、あるいは80~600℃程度の温度で、通常、5~240分程度加熱して乾燥することにより、ガラス質または巨大高分子の絶縁膜を形成することができる。この際の加熱方法としては、ホットプレート、オーブン、ファーンネスなどを使用することが出来、加熱雰囲気としては、大気下、窒素雰囲気、アルゴ

ン雰囲気、真空下、酸素濃度をコントロールした減圧下などで行うことができる。

【0034】このようにして得られる層間絶縁膜は、絶縁性に優れ、塗布膜の均一性、誘電率特性、塗膜の耐クラック性、塗膜の表面硬度に優れることから、LSI、システムLSI、DRAM、SDRAM、RDRAM、D-RDRAMなどの半導体素子用層間絶縁膜、半導体素子の表面コート膜などの保護膜、多層レジストを用いた半導体作製工程の中間層、多層配線基板の層間絶縁膜、液晶表示素子用の保護膜や絶縁膜などの用途に有用である。

【0035】

【実施例】以下、実施例を挙げて、本発明をさらに具体的に説明する。なお、実施例および比較例中の部および%は、特記しない限り、それぞれ重量部および重量%であることを示している。また、実施例中における膜形成用組成物の評価は、次のようにして測定したものである。

【0036】重量平均分子量 (Mw)

下記条件によるゲルパーミエーションクロマトグラフィー (GPC) 法により測定した。

試料：テトラヒドロフランを溶媒として使用し、加水分解縮合物1gを、100ccのテトラヒドロフランに溶解して調製した。

標準ポリスチレン：米国プレッシャーケミカル社製の標準ポリスチレンを使用した。

装置：米国ウオーターズ社製の高温高速ゲル浸透クロマトグラム (モデル150-C ALC/GPC)

カラム：昭和電工 (株) 製のSHODEX A-80M (長さ50cm)

測定温度：40℃

流速：1cc/分

【0037】機械的強度 (弾性率)

塗膜形成用組成物を、8インチシリコンウエハ上にスピコーターを用いて、回転数1,500rpm、30秒の条件で以て塗布した。ホットプレート上で70℃で3分間、200℃で3分間基板を乾燥し、さらに400℃の窒素雰囲気のホットプレート上で30分基板を焼成した。得られた塗膜の弾性率はナノインデントXP (ナノインストルメンツ社製) を用いて、連続剛性測定法により測定した。

【0038】短時間焼成 (脱離ガス量測定)

塗膜形成用組成物を、8インチシリコンウエハ上にスピコーターを用いて、回転数1,500rpm、30秒の条件で以て塗布した。ホットプレート上で70℃で3分間、200℃で3分間基板を乾燥し、さらに400℃の窒素雰囲気のホットプレート上で10分基板を焼成した。得られた基板を電子科学 (株) 製昇温打つりガス分析装置EMD-WA1000Sを用いて400℃まで加熱し脱離したガスを測定した。脱離ガス量をCVDによ

り形成されたSiO₂膜と比較し、下記基準で評価した。

○：脱離ガス量がCVDにより形成されたSiO₂膜以下

×：脱離ガス量がCVDにより形成されたSiO₂膜を越える

【0039】誘電率

塗膜形成用組成物を、8インチシリコンウエハ上にスピコーターを用いて、回転数1,500rpm、30秒の条件で以て塗布した。ホットプレート上で70℃で3分間、200℃で3分間基板を乾燥し、さらに400℃の窒素雰囲気のホットプレート上で30分基板を焼成した。得られた基板の上にアルミニウムを蒸着し、誘電率評価用基板を作製した。誘電率は、横川・ヒューレットパカード (株) 製のHP16451B電極およびHP4284AプレジジョンLCRメーターを用いて、10kHzにおける容量値から算出した。

【0040】合成例1

石英製セパラブルフラスコ中で、メチルトリメトキシシラン308.5gとテトラメトキシシラン96.5gとジイソプロポキシチタンビスエチルアセチルアセテート0.95gを、プロピレングリコールモノメチルエーテル500gに溶解させたのち、スリーワンモーターで攪拌させ、溶液温度60℃に安定させた。次に、イオン交換水84gを2時間かけて溶液に添加した。その後、60℃で2時間反応させたのち、反応液を室温まで冷却した。この反応液に、プロピレングリコールモノメチルエーテル595gを添加し、50℃で反応液からメタノールを含む溶液を595gエバポレーションで除去し、反応液①を得た。このようにして得られた縮合物等の重量平均分子量は、7,800であった。

【0041】合成例2

石英製セパラブルフラスコ中で、メチルトリメトキシシラン308.5gとテトラメトキシシラン96.5gをプロピレングリコールモノエチルエーテル545gに溶解させたのち、スリーワンモーターで攪拌させ、溶液温度を60℃に安定させた。次に、マレイン酸10.0gを溶解させたイオン交換水42gを2時間かけて溶液に添加した。その後、60℃で2時間反応させたのち、反応液を室温まで冷却した。この反応液に、プロピレングリコールモノエチルエーテル595gを添加し、50℃で反応液からメタノールを含む溶液を595gエバポレーションで除去し、反応液②を得た。このようにして得られた縮合物等の重量平均分子量は、3,200であった。

【0042】実施例1

合成例1で得られた反応液①100gにトリエチレングリコールモノエチルエーテル16gとSI-L85 (三新化学工業 (株) 製) 0.2gを添加し、十分攪拌した。0.2μm孔径のテフロン製フィルターでろ過を行

い本発明の膜形成用組成物を得た。得られた組成物をスピコート法でシリコンウエハ上に塗布した。得られた塗膜の弾性率は5.4 GPaと機械的強度に優れていた。塗膜の脱離ガス量を測定したところ、CVDにより形成されたSiO₂膜以下と短時間焼成でも少ない脱離ガス量であった。また、塗膜の誘電率を評価したところ、2.43と非常に低い誘電率を示した。

ろ、2.43と非常に低い誘電率を示した。

【0043】実施例2～6

表1に示す組成で膜形成用組成物を作製し、実施例1と同様に評価を行った。評価結果を表1に併せて示す。

【0044】

【表1】

実施例	反応液	(B)成分	(C)成分	弾性率 (GPa)	脱離ガス量	誘電率
1	反応液 ①100g	SI-L85 0.2g	トリエチレングリコールモノエーテル 16g	5.4	○	2.43
2	反応液 ②100g	トリエチレングリコールモノエーテル 16g 3,5-ジメチルベンゾ酸 0.2g	トリエチレングリコールモノエーテル 16g	5.7	○	2.49
3	反応液 ②100g	[(α,α-ジメチル-3,5-ジメチルベンゾ酸)メチル]アミン 0.2g	トリエチレングリコールモノエーテル 16g	5.2	○	2.48
4	反応液 ②100g	SI-L85 0.2g	トリエチレングリコールモノエーテル 16g	5.8	○	2.47
5	反応液 ①100g	SI-L150 0.5g	トリエチレングリコールモノエーテル 16g	5.3	○	2.44
6	反応液 ①	[(α,α-ジメチル-3,5-ジメチルベンゾ酸)メチル]アミン 0.2g	トリエチレングリコールモノエーテル 8g	5.0	○	2.49

【0045】実施例7

合成例1で得られた反応液①100gにトリエチレングリコールモノエーテル16gとSI-L85（三新化学工業（株）製）0.2gとアセチルアセトン4gを添加し十分攪拌した。0.2μm孔径のテフロン製フィルターでろ過を行い本発明の膜形成用組成物を得た。得られた組成物をスピコート法でシリコンウエハ上に塗布した。得られた塗膜の弾性率は5.3 GPaと機械的強度に優れていた。塗膜の脱離ガス量を測定したところ、CVDにより形成されたSiO₂膜以下と短時間焼成でも少ない脱離ガス量であった。また、塗膜の誘電率を評価したところ、2.42と非常に低い誘電率を示した。

【0046】実施例8

合成例1で得られた反応液①100gにトリエチレングリコールモノエーテル16gとSI-L85（三新化学工業（株）製）0.2gと重量分子量約2,000のポリエチレングリコール10gを添加し十分攪拌し

た。0.2μm孔径のテフロン製フィルターでろ過を行い本発明の膜形成用組成物を得た。得られた組成物をスピコート法でシリコンウエハ上に塗布した。得られた塗膜の弾性率は5.1 GPaと機械的強度に優れていた。塗膜の脱離ガス量を測定したところ、CVDにより形成されたSiO₂膜以下と短時間焼成でも少ない脱離ガス量であった。また、塗膜の誘電率を評価したところ、2.12と非常に低い誘電率を示した。

【0047】実施例9

合成例1で得られた反応液①100gにトリエチレングリコールモノエーテル16gとSI-L85（三新化学工業（株）製）0.2gと重量分子量約4,000のポリメタクリル酸イソプロピル10gを添加し十分攪拌した。0.2μm孔径のテフロン製フィルターでろ過を行い本発明の膜形成用組成物を得た。得られた組成物をスピコート法でシリコンウエハ上に塗布した。得られた塗膜の弾性率は5.0 GPaと機械的強度に優れていた。塗膜の脱離ガス量を測定したところ、CVD

により形成された SiO_2 膜以下と短時間焼成でも少ない脱離ガス量であった。また、塗膜の誘電率を評価したところ、2.15と非常に低い誘電率を示した。

【0048】比較例1

合成例1で得られた反応液①のみを使用した以外は、実施例1と同様にして評価を行った。塗膜の誘電率を測定したところ、2.65と比較的低い誘電率であったが、得られた塗膜の弾性率は2.9GPaと機械的強度に劣るものであった。また、塗膜の脱離ガス量を測定したところ、CVDにより形成された SiO_2 膜より多い脱離

【0049】比較例2

合成例1で得られた反応液①にトリエチレングリコールモノエチルエーテル16gのみ添加した以外は、実施例1と同様にして評価を行った。塗膜の誘電率を測定したところ、2.67と比較的低い誘電率であったが、得られた塗膜の弾性率は2.7GPaと機械的強度に劣るものであった。また、塗膜の脱離ガス量を測定したとこ

フロントページの続き

(72)発明者 袴塚 聡子

東京都中央区築地二丁目11番24号 ジェイエスアール株式会社内

(72)発明者 山田 欣可

東京都中央区築地二丁目11番24号 ジェイエスアール株式会社内

ろ、CVDにより形成された SiO_2 膜より多い脱離ガス量を示した。

【0050】比較例3

合成例1で得られた反応液①にSI-L85（三新化学工業（株）製）0.2gのみ添加した以外は、実施例1と同様にして評価を行った。得られた塗膜の弾性率は5.1GPaと高い値であったが、塗膜の誘電率を測定したところ、3.02と高い誘電率を示した。また、塗膜の脱離ガス量を測定したところ、CVDにより形成された SiO_2 膜より多い脱離ガス量を示した。

【0051】

【発明の効果】本発明によれば、アルコキシシランの加水分解物および/またはその縮合物と、常圧での沸点が180℃以上の溶剤と、潜在性酸発生触媒および/または潜在性塩基発生触媒を含有する組成物で、塗膜の機械的特性に優れ、短時間で塗膜の焼成が可能であり、非常に低い誘電率を示す膜形成用組成物（層間絶縁膜用材料）を提供することが可能である。

Fターム(参考) 4J038 CG142 DF022 DL021 DL031
JA34 KA04 KA06 NA21
4J040 DF041 DF042 DF051 DF052
EE022 EK051 EK071 HB10
HB11 HB15 HB20 HB24 HB31
HD13 HD21 HD41 KA14 KA23
LA05 LA06 LA09
4M104 EE18 HH20
5F033 RR21 SS22 WW03 WW04 XX17
XX24
5F058 AA10 AC03 AF04 AG01 AH01
AH02

* NOTICES *

JPO and NCIPi are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] (A) (A-1) The compound and $R_1aSi(OR_2)_4$ -a which are expressed with the following general formula (1) (1)

(R_1 shows a hydrogen atom, a fluorine atom, or a univalent organic radical, R_2 shows a univalent organic radical, and a expresses the integer of 0-2.)

(A-2) Following general formula (2) $R_3b(R_4O)_3-bSi-(R_7)_d-Si(OR_5)_3-cR_6c$ Compound expressed ...

(2) (R_3 , R_4 , R_5 , and R_6) you may differ, even if the same, a univalent organic radical is shown, respectively, even if b and c are the same, you may differ, and the number of 0-2 is shown, R_7 shows the radical expressed with an oxygen atom or $-(CH_2)_n$ -, and, in n , 1-6d show 0 or 1. from -- the hydrolyzate of at least one sort of compounds chosen from the becoming group and a condensate, or either -- the constituent for film formation characterized by the boiling point in (B) latency acid catalyst and a latency base catalyst or either, and (C) ordinary pressure containing a solvent 180 degrees C or more.

[Claim 2] (D) The constituent for film formation according to claim 1 characterized by the boiling point in ordinary pressure containing a solvent 160 degrees C or less further.

[Claim 3] (B) The constituent for film formation according to claim 1 with which the operating rate of a component is characterized by being 0.001 - 10 weight section to the (A) component 100 weight section (full hydrolysis condensate conversion).

[Claim 4] (C) The constituent for film formation according to claim 1 characterized by choosing a component from polyhydric alcohol, a glycol system solvent, a glycol monoalkyl ether system solvent, a glycol dialkyl ethers solvent, a glycol monoalkyl ether ester solvent, and a glycol diester system solvent.

[Claim 5] The constituent for film formation according to claim 1 with which the (C) component in a constituent and (D) component use rate are characterized by being (C):(D) = 5:95-50:50 (a weight ratio, a (C) component + (D) component = 100).

[Claim 6] The constituent for film formation according to claim 1 characterized by containing at least one sort of compounds chosen from the group which consists of the compound and (meta) the acrylic polymer which furthermore have beta-diketone and polyalkylene oxide structure.

[Claim 7] The charge of insulator layer formation material characterized by consisting of a constituent for film formation according to claim 1 to 6.

[Translation done.]

* NOTICES *

JPO and NCIPi are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

DETAILED DESCRIPTION

[Detailed Description of the Invention]

[0001]

[Field of the Invention] About the constituent for film formation, in more detail, as an interlayer insulation film ingredient in a semiconductor device etc., this invention is excellent in the mechanical property of a paint film, and baking of a paint film is possible for it in a short time, and it relates to the constituent for film formation in which a very low dielectric constant is shown.

[0002]

[Description of the Prior Art] Conventionally, the silica (SiO_2) film which is vacuum processes, such as a CVD method, with was formed as an interlayer insulation film in a semiconductor device etc. is used abundantly. And the insulator layer of the spreading mold which uses as a principal component the hydrolysis product of the tetra-alkoxy run called the SOG (Spin on Glass) film for the purpose of forming a recent years more uniform interlayer insulation film is also used. Moreover, the interlayer insulation film of a low dielectric constant which uses as a principal component polyorganosiloxane called organic [SOG] is developed with high integration of a semiconductor device etc. however, the conductor which was more excellent with the further high integration and the further multilayering of a semiconductor device etc. -- the interlayer insulation film ingredient which the electric insulation of a between is demanded, therefore is more excellent in a low dielectric constant at a mechanical strength is called for.

[0003] So, the spreading setup-of-tooling product for insulator layer formation of a low dielectric constant is indicated by JP,6-181201,A as an interlayer insulation film ingredient. This spreading setup-of-tooling product has low absorptivity, it aims at offering the insulator layer of a semiconductor device excellent in crack-proof nature, and that configuration is a spreading setup-of-tooling product for insulator layer formation with which the number average molecular weight to which it comes to carry out condensation polymerization of the organometallic compound containing at least one sort of elements chosen from titanium, a zirconium, niobium, and a tantalum and the organic silicon compound which has at least one alkoxy group in intramolecular uses 500 or more oligomer as a principal component.

[0004] Moreover, thick-film spreading which becomes WO 96/No. 00758 official report from metal alkoxides, organic solvents, etc. other than alkoxysilane and a silane which are used for formation of the interlayer insulation film of a multilayer-interconnection substrate is possible, and the charge of silica system spreading mold insulator layer formation material which is excellent in oxygen-proof plasma nature is indicated.

[0005] Furthermore, the useful coating liquid for oxide coat formation is indicated by surface flattening, such as electronic parts, layer insulation, etc. at JP,3-20377,A. Even if this coating liquid for oxide coat formation is the case where hardening in an elevated temperature and processing by the oxygen plasma are performed by offering uniform coating liquid without generating of a gel object, and using this coating liquid, it aims at obtaining a good oxide coat without a crack. And the configuration is coating liquid for oxide coat formation which hydrolyzes a predetermined silane compound and the same

predetermined chelate compound by organic solvent's existence-ization, and is obtained by carrying out a polymerization.

[0006] However, when metal chelate compound, such as titanium and a zirconium, is combined with a silane compound as mentioned above, it does not have baking of a paint film, a very low dielectric constant, etc. with sufficient balance in the mechanical property of a paint film, and a short time.

[0007]

[Problem(s) to be Solved by the Invention] About the constituent for film formation for solving the above-mentioned trouble, as an interlayer insulation film in a semiconductor device etc., this invention is excellent in the mechanical property of a paint film, and baking of a paint film is possible for it in a short time, and it aims still more detailed at offering the very low charge of dielectric constant **** interlayer insulation film material.

[0008] This invention is compound $R_1aSi(OR_2)_4$ -a expressed with the (A) (A-1) following general formula (1)..... (1)

(R1 shows a hydrogen atom, a fluorine atom, or a univalent organic radical, R2 shows a univalent organic radical, and a expresses the integer of 0-2.) And (A-2) the following general formula (2) Compound expressed $R_3b(R_4O)_3-bSi-(R_7)_d-Si(OR_5)_3-cR_6c$ (2) (you may differ, even if R3, R4, R5, and R6 are the same, and a univalent organic radical is shown, respectively b and c) you may differ, even if the same, and the number of 0-2 is shown, R7 shows the radical expressed with an oxygen atom or $-(CH_2)_n-$, and, as for 1-6d, n shows 0 or 1. from -- the hydrolyzate of at least one sort of compounds chosen -- And it crawls and the constituent for film formation and the charge of insulator layer formation material which are characterized by the thing which also spread a condensate, and for which the boiling point in (B) latency acid catalyst and a latency base catalyst or either, and (C) ordinary pressure, on the other hand, contains a solvent 180 degrees C or more in a gap are offered.

[0009]

[Embodiment of the Invention]

[0010] (A) In the component (A-1) component above-mentioned general formula (1), an alkyl group, an aryl group, an allyl group, a glycidyl group, etc. can be mentioned as a univalent organic radical of R1 and R2. Moreover, as for R1, in a general formula (1), it is desirable that it is an organic radical especially a univalent alkyl group, or a univalent phenyl group. Here, as an alkyl group, a methyl group, an ethyl group, a propyl group, butyl, etc. are mentioned, it is carbon numbers 1-5 preferably, and these alkyl groups may branch also by the shape of a chain, and the hydrogen atom may be further permuted by the fluorine atom etc. In a general formula (1), a phenyl group, a naphthyl group, a methylphenyl radical, an ethyl phenyl group, a chlorophenyl radical, a BUROMO phenyl group, a fluoro phenyl group, etc. can be mentioned as an aryl group.

[0011] As an example of a compound expressed with a general formula (1) Trimethoxysilane, triethoxysilane, tree n-propoxysilane, Tree iso-propoxysilane, tree n-butoxysilane, tree sec-butoxysilane, Tree tert-butoxysilane, triphenoxysilane, fluoro trimethoxysilane, Fluoro triethoxysilane, fluoro tree n-propoxysilane, Fluoro tree iso-propoxysilane, fluoro tree n-butoxysilane, Fluoro tree sec-butoxysilane, fluoro tree tert-butoxysilane, Fluoro triphenoxysilane, a tetramethoxy silane, a tetra-ethoxy silane, Tetra-n-propoxysilane, tetra--iso-propoxysilane, A tetra--n-butoxy run, tetra--sec-butoxysilane, tetra--tert-butoxysilane, Tetra-phenoxy silane etc.; Methyl trimetoxysilane, methyl triethoxysilane, Methyl tree n-propoxysilane, methyl tree iso-propoxysilane, Methyl tree n-butoxysilane, methyl tree sec-butoxysilane, Methyl tree tert-butoxysilane, methyl triphenoxysilane, Ethyltrimethoxysilane, ethyltriethoxysilane, ethyl tree n-propoxysilane, Ethyl tree iso-propoxysilane, ethyl tree n-butoxysilane, Ethyl tree sec-butoxysilane, ethyl tree tert-butoxysilane, Ethyl triphenoxysilane, vinyltrimetoxysilane, vinyltriethoxysilane, Vinyl tree n-propoxysilane, vinyl tree iso-propoxysilane, Vinyl tree n-butoxysilane, vinyl tree sec-butoxysilane, Vinyl tree tert-butoxysilane, vinyl triphenoxysilane, n-propyltrimethoxysilane, n-propyl triethoxysilane, n-propyl tree n-propoxysilane, n-propyl tree iso-propoxysilane, n-propyl tree n-butoxysilane, n-propyl tree sec-butoxysilane, n-propyl tree tert-butoxysilane, n-propyl triphenoxysilane, i-propyltrimethoxysilane, i-propyl triethoxysilane, i-propyl tree n-propoxysilane, i-propyl tree iso-propoxysilane, i-propyl tree n-butoxysilane, i-propyl tree sec-

butoxysilane, i-propyl tree tert-butoxysilane, i-propyl triphenoxysilane, n-butyltrimethoxysilane, n-butyltriethoxysilane, n-butyl tree n-propoxysilane, n-butyl tree iso-propoxysilane, n-butyl tree n-butoxysilane, n-butyl tree sec-butoxysilane, n-butyl tree tert-butoxysilane, n-butyl triphenoxysilane, sec-butyltrimethoxysilane, sec-butyl-i-triethoxysilane, sec-butyl-tree n-propoxysilane, sec-butyl-tree iso-propoxysilane, sec-butyl-tree n-butoxysilane, sec-butyl-tree sec-butoxysilane, sec-butyl-tree tert-butoxysilane, sec-butyl-triphenoxysilane, t-butyltrimethoxysilane, T-butyltriethoxysilane, t-butyl tree n-propoxysilane, t-butyl tree iso-propoxysilane, t-butyl tree n-butoxysilane, t-butyl tree sec-butoxysilane, t-butyl tree tert-butoxysilane, t-butyl triphenoxysilane, phenyltrimethoxysilane, phenyltriethoxysilane, Phenyl tree n-propoxysilane, phenyl tree iso-propoxysilane, Phenyl tree n-butoxysilane, phenyl tree sec-butoxysilane, Phenyl tree tert-butoxysilane, phenyl triphenoxysilane, Vinyltrimethoxysilane, vinyltriethoxysilane, gamma-aminopropyl trimethoxysilane, gamma-aminopropyl triethoxysilane, gamma-glycidoxypropyltrimethoxysilane, gamma-glycidoxy propyltriethoxysilane, gamma-truffe ROROPURO pill trimethoxysilane, gamma-truffe ROROPURO pill triethoxysilane etc.;

Dimethyldimethoxysilane, Dimethyl diethoxysilane, dimethyl-G n-propoxysilane, Dimethyl-G iso-propoxysilane, dimethyl-G n-butoxysilane, Dimethyl-G sec-butoxysilane, dimethyl-G tert-butoxysilane, A JIMECHIRUJI phenoxy silane, diethyldimethoxysilane, diethyldiethoxysilane, Diethyl-G n-propoxysilane, diethyl-G iso-propoxysilane, Diethyl-G n-butoxysilane, diethyl-G sec-butoxysilane, Diethyl-G tert-butoxysilane, a JIECHIRUJI phenoxy silane, G n-propyl dimethoxysilane, di-n-propyl diethoxysilane, G n-propyl-G n-propoxysilane, G n-propyl-G iso-propoxysilane, G n-propyl-G n-butoxysilane, G n-propyl-G sec-butoxysilane, G n-propyl-G tert-butoxysilane, a G n-propyl-G phenoxy silane, G iso-propyl dimethoxysilane, G iso-propyl diethoxysilane, G iso-propyl-G n-propoxysilane, G iso-propyl-G iso-propoxysilane, G iso-propyl-G n-butoxysilane, G iso-propyl-G sec-butoxysilane, G iso-propyl-G tert-butoxysilane, a G iso-propyl-G phenoxy silane, Di-n-butyl dimethoxysilane, di-n-butyl diethoxysilane, di-n-butyl-G n-propoxysilane, di-n-butyl-G iso-propoxysilane, and di-n-butyl-G n-BUTOKISHISHIRA N, di-n-butyl-G sec-butoxysilane, di-n-butyl-G tert-butoxysilane, A di-n-butyl-G phenoxy silane, G sec-butyl dimethoxysilane, G sec-butyl diethoxysilane, G sec-butyl-G n-propoxysilane, G sec-butyl-G iso-propoxysilane, G sec-butyl-G n-butoxysilane, G sec-butyl-G sec-butoxysilane, G sec-butyl-G tert-butoxysilane, A G sec-butyl-G phenoxy silane, G tert-butyl dimethoxysilane, G tert-butyl diethoxysilane, G tert-butyl-G n-propoxysilane, G tert-butyl-G iso-propoxysilane, G tert-butyl-G n-butoxysilane, G tert-butyl-G sec-butoxysilane, G tert-butyl-G tert-butoxysilane, A G tert-butyl-G phenoxy silane, diphenyldimethoxysilane, A diphenyl-G ethoxy silane, diphenyl-G n-propoxysilane, Diphenyl-G iso-propoxysilane, diphenyl-G n-butoxysilane, Diphenyl-G sec-butoxysilane, diphenyl-G tert-butoxysilane, A diphenyl JIFENOKI gardenia fruit run, divinyl trimethoxysilane, gamma-aminopropyl trimethoxysilane, ,, such as gamma-aminopropyl triethoxysilane, gamma-glycidoxypropyltrimethoxysilane, gamma-glycidoxy propyltriethoxysilane, gamma-truffe ROROPURO pill trimethoxysilane, and gamma-truffe ROROPURO pill triethoxysilane, can be mentioned. Preferably A tetramethoxy silane, a tetra-ethoxy silane, tetra--n-propoxysilane, Tetra--iso-propoxysilane, a tetra-phenoxy silane, methyl trimethoxysilane, Methyl triethoxysilane, methyl tree n-propoxysilane, methyl tree iso-propoxysilane, Ethyltrimethoxysilane, ethyltriethoxysilane, vinyltrimethoxysilane, Vinyltriethoxysilane, phenyltrimethoxysilane, phenyltriethoxysilane, Dimethyldimethoxysilane, dimethyl diethoxysilane, diethyldimethoxysilane, Diethyldiethoxysilane, diphenyldimethoxysilane, diphenyl diethoxysilane, They are trimethyl monochrome methoxysilane, a trimethyl monochrome ethoxy silane, triethyl mono-methoxysilane, a triethyl mono-ethoxy silane, triphenyl mono-methoxysilane, and a triphenyl mono-ethoxy silane. These may use one sort or two sorts or more for coincidence.

[0012] (A-2) In the component above-mentioned general formula (2), the same organic radical as a previous general formula (1) can be mentioned as a univalent organic radical. Moreover, as a divalent organic radical which is R7 of a general formula (2), a methylene group, the alkylene group of carbon numbers 2-6, etc. can be mentioned. R7 among general formulas (2) as a compound of an oxygen atom Hexamethoxy disiloxane, hexa ethoxy disiloxane, hexa phenoxy disiloxane, 1, 1, 1, 3, and 3-PENTA methoxy-3-methyl disiloxane, 1, 1, 1 and 3, and 3-pentaethoxy-3-methyl disiloxane, 1, 1, 1, 3, and 3-

PENTA methoxy-3-phenyl disiloxane, 1, 1, 1, 3, and 3-pentaethoxy-3-phenyl disiloxane, 1, 1, 3, and 3-tetramethoxy -1, 3-dimethyl disiloxane, 1, 1, 3, and 3-tetra-ethoxy -1, 3-dimethyl disiloxane, 1, 1, 3, and 3-tetramethoxy -1, 3-diphenyl disiloxane, 1, 1, 3, and 3-tetra-ethoxy -1, 3-diphenyl disiloxane, 1, 1, 3-trimethoxy - 1, 3, and 3-trimethyldisiloxane, 1, 1, 3-TORIETOKISHI - 1, 3, and 3-trimethyldisiloxane, 1, 1, 3-trimethoxy - 1, 3, and 3-triphenyl disiloxane, 1, 1, 3-TORIETOKISHI - 1, 3, and 3-triphenyl disiloxane, 1, 3-dimethoxy - 1, 1, 3, and 3-tetramethyl disiloxane, 1, 3-diethoxy - 1, 1, 3, and 3-tetramethyl disiloxane, 1, 3-dimethoxy - 1, 1, 3, and 3-tetra-phenyl disiloxane, 1, 3-diethoxy - 1, 1, 3, and 3-tetra-phenyl disiloxane etc. can be mentioned. Among these Hexamethoxy disiloxane, hexaethoxy disiloxane, 1, 1, 3, and 3-tetramethoxy -1, 3-dimethyl disiloxane, 1, 1, 3, and 3-tetra-ethoxy -1, 3-dimethyl disiloxane, 1, 1, 3, and 3-tetramethoxy -1, 3-diphenyl disiloxane, 1, 3-dimethoxy - 1, 1, 3, and 3-tetramethyl disiloxane, 1, 3-diethoxy - 1, 1, 3, and 3-tetramethyl disiloxane, 1, 3-dimethoxy - 1, 1, 3, and 3-tetra-phenyl disiloxane, 1, 3-diethoxy - 1, 1, 3, and 3-tetra-phenyl disiloxane etc. can be mentioned as a desirable example. In a general formula (2) d as a compound of 0 A hexamethoxy disilane, a hexaethoxy disilane, a hexa FENIKISHI disilane, A 1, 1, 1, 2, and 2-PENTA methoxy-2-methyl disilane, 1, 1, 1 and 2, and 2-pentaethoxy-2-methyl disilane, A 1, 1, 1, 2, and 2-PENTA methoxy-2-phenyl disilane, 1, 1, 1 and 2, and 2-pentaethoxy-2-phenyl disilane, 1, 1, 2, and 2-tetramethoxy -1, 2-dimethyl disilane, 1, 1 and 2, 2-tetra-ethoxy -1, 2-dimethyl disilane, 1, 1, 2, and 2-tetramethoxy -1, 2-diphenyl disilane, 1, 1 and 2, 2-tetra-ethoxy -1, 2-diphenyl disilane, 1, 1, 2-trimethoxy - A 1, 2, and 2-trimethyl disilane, 1 and 1, 2-TORIETOKISHI - 1, 2, and 2-trimethyl disilane, 1, 1, 2-trimethoxy - 1, 2, and 2-triphenyl disilane, 1 and 1, 2-TORIETOKISHI - 1, 2, and 2-triphenyl disilane, 1, 2-dimethoxy - A 1, 1, 2, and 2-tetramethyl disilane, 1, 2-diethoxy - 1, 1, 2, and 2-tetramethyl disilane, 1, 2-dimethoxy - A 1, 1, 2, and 2-tetra-phenyl disilane, 1, 2-diethoxy - a 1, 1, 2, and 2-tetra-phenyl disilane etc. As a compound of a radical by which R7 is expressed with $-(CH_2)_n-$ in a general formula (2) Screw (hexamethoxy silyl) methane, screw (hexaethoxy silyl) methane, Screw (hexa phenoxy silyl) methane, screw (dimethoxymethyl silyl) methane, Screw (diethoxymethylsilyl) methane, screw (dimethoxy phenyl silyl) methane, Screw (diethoxy phenyl silyl) methane, screw (methoxy dimethylsilyl) methane, Screw (ethoxy dimethylsilyl) methane, screw (methoxy diphenyl silyl) methane, Screw (ethoxy diphenyl silyl) methane, screw (hexamethoxy silyl) ethane, Screw (hexaethoxy silyl) ethane, screw (hexa phenoxy silyl) ethane, Screw (dimethoxymethyl silyl) ethane, screw (diethoxymethylsilyl) ethane, Screw (dimethoxy phenyl silyl) ethane, screw (diethoxy phenyl silyl) ethane, Screw (methoxy dimethylsilyl) ethane, screw (ethoxy dimethylsilyl) ethane, Screw (methoxy diphenyl silyl) ethane, screw (ethoxy diphenyl silyl) ethane, 1, 3-screw (hexamethoxy silyl) propane, 1, 3-screw (hexaethoxy silyl) propane, 1, 3-screw (hexa phenoxy silyl) propane, 1, 3-screw (dimethoxymethyl silyl) propane, 1, 3-screw (diethoxymethylsilyl) propane, 1, 3-screw (dimethoxy phenyl silyl) propane, 1, 3-screw (diethoxy phenyl silyl) propane, 1, 3-screw (methoxy dimethylsilyl) propane, 1, 3-screw (ethoxy dimethylsilyl) propane, 1, 3-screw (methoxy diphenyl silyl) propane, 1, and 3-screw (ethoxy diphenyl silyl) propane etc. can be mentioned. Among these A hexamethoxy disilane, a hexaethoxy disilane, A hexa FENIKISHI disilane, 1, 1 and 2, 2-tetramethoxy -1, 2-dimethyl disilane, 1, 1, 2, and 2-tetra-ethoxy -1, 2-dimethyl disilane, 1, 1 and 2, 2-tetramethoxy -1, 2-diphenyl disilane, 1, 1, 2, and 2-tetra-ethoxy -1, 2-diphenyl disilane, 1, 2-dimethoxy - 1, 1, 2, and 2-tetramethyl disilane, 1, 2-diethoxy - A 1, 1, 2, and 2-tetramethyl disilane, 1, 2-dimethoxy - A 1, 1, 2, and 2-tetra-phenyl disilane, 1, 2-diethoxy - A 1, 1, 2, and 2-tetra-phenyl disilane, screw (HE) KISAMETOKISHI silyl methane, screw (hexaethoxy silyl) methane, screw (dimethoxymethyl silyl) methane, screw (diethoxymethylsilyl) methane, screw (dimethoxy phenyl silyl) methane, screw (diethoxy phenyl silyl) methane, screw (methoxy dimethylsilyl) methane, screw (ethoxy dimethylsilyl) methane, screw (methoxy diphenyl silyl) methane, and screw (ethoxy diphenyl silyl) methane can be mentioned as a desirable example. In this invention, a component (A-1) and (A-2) two or more sorts of components can also be used, respectively, using the above-mentioned (A-1) component and (A-2) a component, or either as a (A) component. [0013] In this invention, hydrolysis is that that by which the R2O-radical contained in the above-mentioned (A) component, an R4O-radical, and all R5O-radicals do not need to be hydrolyzed, for example, only one piece is hydrolyzed, the things by which two or more pieces are hydrolyzed, or such

mixture generate. Although the silanol group of the hydrolyzate of the (A) component condenses condensation, Si-O-Si association is formed in this invention, and extent of what all silanol groups do not need to condense and some [few] silanol groups condensed in this invention, and condensation differs, it is the concept which included generating mixture etc. in addition, the weight average molecular weight of the hydrolysis condensate of the (A) component -- usually -- 1,000-120,000 -- it is 1,200 to about 100,000 preferably.

[0014] Moreover, hydrolysis and in case partial condensation is carried out, a catalyst is used for the (A) component. In this case, as a catalyst to be used, metal chelate compound, an organic acid, an inorganic acid, an organic base, and an inorganic base can be mentioned. As metal chelate compound, for example TORIETOKISHI monochrome (acetylacetonato) titanium, Tree n-propoxy monochrome (acetylacetonato) titanium, tree i-propoxy monochrome (acetylacetonato) titanium, Tree n-butoxy monochrome (acetylacetonato) titanium, tree sec-butoxy monochrome (acetylacetonato) titanium, Tree t-butoxy monochrome (acetylacetonato) titanium, diethoxy screw (acetylacetonato) titanium, G n-propoxy screw (acetylacetonato) titanium, G i-propoxy screw (acetylacetonato) titanium, G n-butoxy screw (acetylacetonato) titanium, G sec-butoxy screw (acetylacetonato) titanium, G t-butoxy screw (acetylacetonato) titanium, mono-ethoxy tris (acetylacetonato) titanium, Monod n-propoxy tris (acetylacetonato) titanium, Monod i-propoxy tris (acetylacetonato) titanium, Monod n-butoxy tris (acetylacetonato) titanium, Monod sec-butoxy tris (acetylacetonato) titanium, Monod t-butoxy tris (acetylacetonato) titanium, tetrakis (acetylacetonato) titanium, TORIETOKISHI monochrome (ethyl acetoacetate) titanium, tree n-propoxy monochrome (ethyl acetoacetate) titanium, Tree i-propoxy monochrome (ethyl acetoacetate) titanium, tree n-butoxy monochrome (ethyl acetoacetate) titanium, Tree sec-butoxy monochrome (ethyl acetoacetate) titanium, Tree t-butoxy monochrome (ethyl acetoacetate) titanium, diethoxy screw (ethyl acetoacetate) titanium, G n-propoxy screw (ethyl acetoacetate) titanium, G i-propoxy screw (ethyl acetoacetate) titanium, G n-butoxy screw (ethyl acetoacetate) titanium, G sec-butoxy screw (ethyl acetoacetate) titanium, G t-butoxy screw (ethyl acetoacetate) titanium, mono-ethoxy tris (ethyl acetoacetate) titanium, Monod n-propoxy tris (ethyl acetoacetate) titanium, Monod i-propoxy tris (ethyl acetoacetate) titanium, Monod n-butoxy tris (ethyl acetoacetate) titanium, Monod sec-butoxy tris (ethyl acetoacetate) titanium, Monod t-butoxy tris (ethyl acetoacetate) titanium, tetrakis (ethyl acetoacetate) titanium, Monochrome (acetylacetonato) tris (ethyl acetoacetate) titanium, Screw (acetylacetonato) screw (ethyl acetoacetate) titanium, Tris (acetylacetonato) monochrome (ethyl acetoacetate) titanium, Titanium chelate compound of **; A TORIETOKISHI monochrome (acetylacetonato) zirconium, A tree n-propoxy monochrome (acetylacetonato) zirconium, A tree i-propoxy monochrome (acetylacetonato) zirconium, A tree n-butoxy monochrome (acetylacetonato) zirconium, A tree sec-butoxy monochrome (acetylacetonato) zirconium, A tree t-butoxy monochrome (acetylacetonato) zirconium, A diethoxy screw (acetylacetonato) zirconium, a G n-propoxy screw (acetylacetonato) zirconium, A G i-propoxy screw (acetylacetonato) zirconium, A G n-butoxy screw (acetylacetonato) zirconium, a G sec-butoxy screw (acetylacetonato) zirconium, A G t-butoxy screw (acetylacetonato) zirconium, a mono-ethoxy tris (acetylacetonato) zirconium, A Monod n-propoxy tris (acetylacetonato) zirconium, A Monod i-propoxy tris (acetylacetonato) zirconium, A Monod n-butoxy tris (acetylacetonato) zirconium, A Monod sec-butoxy tris (acetylacetonato) zirconium, A Monod t-butoxy tris (acetylacetonato) zirconium, A tetrakis (acetylacetonato) zirconium, a TORIETOKISHI monochrome (ethyl acetoacetate) zirconium, A tree n-propoxy monochrome (ethyl acetoacetate) zirconium, A tree i-propoxy monochrome (ethyl acetoacetate) zirconium, A tree n-butoxy monochrome (ethyl acetoacetate) zirconium, A tree sec-butoxy monochrome (ethyl acetoacetate) zirconium, A tree t-butoxy monochrome (ethyl acetoacetate) zirconium, A diethoxy screw (ethyl acetoacetate) zirconium, a G n-propoxy screw (ethyl acetoacetate) zirconium, A G i-propoxy screw (ethyl acetoacetate) zirconium, A G n-butoxy screw (ethyl acetoacetate) zirconium, A G sec-butoxy screw (ethyl acetoacetate) zirconium, A G t-butoxy screw (ethyl acetoacetate) zirconium, A mono-ethoxy tris (ethyl acetoacetate) zirconium, a Monod n-propoxy tris (ethyl acetoacetate) zirconium, a Monod i-propoxy tris (ethyl acetoacetate) zirconium, Monod An n-butoxy tris (ethyl acetoacetate) zirconium, a Monod sec-butoxy tris (ethyl acetoacetate) zirconium, A Monod t-butoxy tris (ethyl

acetoacetate) zirconium, A tetrakis (ethyl acetoacetate) zirconium, a monochrome (acetylacetonato) tris (ethyl acetoacetate) zirconium, A screw (acetylacetonato) screw (ethyl acetoacetate) zirconium, A tris (acetylacetonato) monochrome (ethyl acetoacetate) zirconium, The zirconium chelate compound of **; aluminum chelate compound [, such as tris (acetylacetonato) aluminum and tris (ethyl acetoacetate) aluminum,]; etc. can be mentioned. As an organic acid, for example An acetic acid, a propionic acid, butanoic acid, pentanoic acid, A hexanoic acid, oenanthic acid, an octanoic acid, nonoic acid, a decanoic acid, oxalic acid, A maleic acid, a methylmalonic acid, an adipic acid, a sebacic acid, a gallic acid, Butanoic acid, a merit acid, an arachidonic acid, a MIKIMI acid, 2-ethylhexanoic acid, Oleic acid, stearin acid, linolic acid, the Reno Laing acid, a salicylic acid, A benzoic acid, p-aminobenzoic acid, p-toluenesulfonic acid, benzenesulfonic acid, monochloroacetic acid, dichloroacetic acid, a trichloroacetic acid, trifluoroacetic acid, a formic acid, a malonic acid, a sulfonic acid, a phthalic acid, a fumaric acid, a citric acid, a tartaric acid, etc. can be mentioned. As an inorganic acid, a hydrochloric acid, a nitric acid, a sulfuric acid, fluoric acid, a phosphoric acid, etc. can be mentioned, for example. As an organic base, a pyridine, a pyrrole, a piperazine, a pyrrolidine, a piperidine, picoline, a trimethylamine, triethylamine, monoethanolamine, diethanolamine, dimethyl monoethanolamine, monomethyl diethanolamine, triethanolamine, a diaza BISHIKU roke run, a diazabicyclo nonane, diazabicycloundecen, tetramethylammonium hydroxide, etc. can be mentioned, for example. As an inorganic base, ammonia, a sodium hydroxide, a potassium hydroxide, a barium hydroxide, a calcium hydroxide, etc. can be mentioned, for example. Among these catalysts, metal chelate compound, an organic acid, and an inorganic acid are desirable, and can mention titanium chelate compound and an organic acid more preferably. These may use one sort or two sorts or more for coincidence.

[0015] the amount of the above-mentioned catalyst used -- the (A) component (full hydrolysis condensate conversion) -- respectively -- the 100 weight sections -- receiving -- usually -- 0.001 - 10 weight section -- it is the range of 0.01 - 10 weight section preferably. Moreover, you may add beforehand in said solvent, and a catalyst may be underwater dissolved or distributed at the time of water addition.

[0016] (B) The constituent for film formation of component this invention contains a latency acid catalyst and a latency base catalyst, or either. As a latency acid catalyst, a heat acid generator, a photo-oxide generating agent, etc. can be mentioned, for example. 50-450 degrees C of heat acid generators are usually the compound which generates an acid by heating at 200-350 degrees C preferably, and onium salts, such as sulfonium salt, a benzothiazolium salt, ammonium salt, and phosphonium salt, are used.

[0017] As an example of the above-mentioned sulfonium salt, it is 4-aceto phenyl dimethyl sulfonium Hexafluoroantimonate, 4-acetoxyphenyl dimethyl sulfonium Hexafluoroarsenate, Dimethyl-4-(benzyloxy carbonyloxy) phenyl sulfonium Hexafluoroantimonate, Dimethyl-4-(benzoyloxy) phenyl sulfonium Hexafluoroantimonate, Dimethyl-4-(benzoyloxy) phenyl sulfonium Hexafluoroarsenate, Dimethyl-3-chloro-4-acetoxyphenyl sulfonium Alkyl sulfonium salt, such as hexafluoroantimonate; benzyl-4-hydroxy phenylmethyl sulfonium Hexafluoroantimonate, Benzyl-4-hydroxy phenylmethyl sulfonium Hexafluorophosphate, 4-acetoxyphenyl benzyl methyl sulfonium Hexafluoroantimonate, Benzyl-4-methoxy phenylmethyl sulfonium Hexafluoroantimonate, Benzyl-2-methyl-4-hydroxy phenylmethyl sulfonium Hexafluoroantimonate, Benzyl-3-chloro-4-hydroxy phenylmethyl sulfonium Hexafluoroarsenate, Benzyl sulfonium salt, such as 4-methoxybenzyl-4-hydroxy phenylmethyl sulfonium hexafluorophosphate, benzoin tosylate, and 2-nitrobenzyl tosylate;

[0018] Dibenzyl-4-hydroxyphenyl sulfonium Hexafluoroantimonate, Dibenzyl-4-hydroxyphenyl sulfonium Hexafluorophosphate, 4-acetoxyphenyl dibenzyl sulfonium Hexafluoroantimonate, Dibenzyl-4-methoxyphenyl sulfonium Hexafluoroantimonate, Dibenzyl-3-chloro-4-hydroxyphenyl sulfonium Hexafluoroarsenate, Dibenzyl -3 - Methyl-4-hydroxy-5-tert-buthylphenyl sulfonium Hexafluoroantimonate, Benzyl-4-methoxybenzyl-4-hydroxyphenyl sulfonium Dibenzyl sulfonium salt, such as hexafluorophosphate; p-chloro benzyl-4-hydroxy phenylmethyl sulfonium Hexafluoroantimonate, p-nitrobenzyl-4-hydroxy phenylmethyl sulfonium Hexafluoroantimonate, p-chloro benzyl-4-hydroxy phenylmethyl sulfonium Hexafluorophosphate, p-nitrobenzyl-3-methyl-4-hydroxy phenylmethyl sulfonium Hexafluoroantimonate, 3, 5-dichloro benzyl-4-hydroxy phenylmethyl

sulfonium Hexafluoroantimonate, o - Chloro benzyl-3-chloro-4-hydroxy phenylmethyl sulfonium Permutation benzyl sulfonium salt, such as hexafluoroantimonate;

[0019] As an example of the above-mentioned benzothia ZONIUMU salt, 3-benzyl benzothiazolium hexafluoroantimonate, 3-benzyl benzothiazolium Hexafluorophosphate, 3-benzyl benzothiazolium Tetrafluoroborate, 3-(p-methoxybenzyl) benzothiazolium Hexafluoroantimonate, 3-benzyl-2-methylthio benzothiazolium Hexafluoroantimonate, 3-benzyl-5-chlorobenzo thiazolium Benzyl benzothiazolium salts, such as hexafluoroantimonate, are mentioned. Furthermore, 2, 4, 4, and 6-tetrabromo cyclohexa JIENON can be illustrated as heat acid generators other than the above.

[0020] It is 4-acetoxyphenyl dimethyl sulfonium among these. Hexafluoroarsenate, benzyl-4-hydroxy phenylmethyl sulfonium Hexafluoroantimonate, 4-acetoxyphenyl benzyl methyl sulfonium Hexafluoroantimonate, dibenzyl-4-hydroxyphenyl sulfonium Hexafluoroantimonate, 4-acetoxyphenyl benzyl sulfonium Hexafluoroantimonate, 3-benzyl benzothiazolium hexafluoroantimonate, etc. are used preferably. As these commercial items, it is SAN-AID. SI-L85, this SI-L110, this SI-L145, this SI-L150, this SI-L160 (product made from 3 Japanese Federation of Chemical Industry Workers' Unions Industry), etc. are mentioned. these compounds are independent -- it is -- two or more sorts can be combined and it can use.

[0021] The latency photo-oxide generating agent used by this invention is a compound which usually generates an acid by the ultraviolet radiation exposure of 10-50mJ preferably one to 100 mJ. As a photo-oxide generating agent, for example Diphenyliodonium trifluoromethane sulfonate, Diphenyliodonium pyrene sulfonate, diphenyliodonium dodecylbenzene sulfonate, Diphenyliodonium nona fluoro n-butane sulfonate, screw (4-t-buthylphenyl) iodonium trifluoromethane sulfonate, Screw (4-t-buthylphenyl) iodonium dodecylbenzene sulfonate, Screw (4-t-buthylphenyl) iodonium naphthalene sulfonate, Screw (4-t-buthylphenyl) iodonium hexafluoroantimonate, Screw (4-t-buthylphenyl) iodonium nona fluoro n-butane sulfonate, Triphenylsulfonium trifluoromethane sulfonate, triphenylsulfonium hexafluoroantimonate, Triphenylsulfonium naphthalene sulfonate, triphenylsulfonium nona fluoro-n-butane sulfonate, Diphenyl (4-methylphenyl) sulfonium trifluoromethane sulfonate, Diphenyl (4-methoxyphenyl) sulfonium trifluoromethane sulfonate, Benzene methyl sulfonium toluenesulfonate, (Hydroxyphenyl) Cyclohexyl methyl (2-oxocyclohexyl) sulfonium trifluoromethane sulfonate, Dicyclohexyl (2-oxocyclohexyl) sulfonium trifluoromethane sulfonate, Dimethyl (2-oxocyclohexyl) sulfonium trifluoromethane sulfonate, Diphenyliodonium hexafluoroantimonate, triphenylsulfonium camphor sulfonate, Benzyl methyl sulfonium toluenesulfonate, (4-hydroxyphenyl) 1-NAFUCHIRUJIMECHIRU sulfonium trifluoromethane sulfonate, 1-NAFUCHIRUJIECHIRU sulfonium trifluoromethane sulfonate, 4-SHIANO 1-NAFUCHIRUJIMECHIRU sulfonium trifluoromethane sulfonate, 4-nitro-1-NAFUCHIRUJIMECHIRU sulfonium trifluoromethane sulfonate, 4-methyl-1-NAFUCHIRUJIMECHIRU sulfonium trifluoromethane sulfonate, 4-cyano-1-naphthyl-diethyl sulfonium trifluoromethane sulfonate, 4-nitro-1-NAFUCHIRUJIECHIRU sulfonium trifluoromethane sulfonate, 4-methyl-1-NAFUCHIRUJIECHIRU sulfonium trifluoromethane sulfonate, 4-hydroxy-1-NAFUCHIRUJIMECHIRU sulfonium trifluoromethane sulfonate, 4-hydroxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-methoxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-ethoxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-methoxy methoxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-ethoxy methoxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-(1-methoxyethoxy)-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-(2-methoxyethoxy)-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-methoxycarbonyloxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4 - Ethoxy cull BUNIRU oxy--1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-n-propoxycarbonyloxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-i-propoxycarbonyloxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-n-BUTOKI carbinyl oxy--1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-t-buthoxycarbonyloxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-(2-tetrahydrofuranlyl oxy-)-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-(2-

tetrahydropyranyloxy)-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, 4-benzyloxy-1-naphthyl tetrahydro CHIOFENIUMU trifluoromethane sulfonate, Onium salt system photo-oxide generating agents, such as 1-(naphthyl aceto methyl) tetrahydro CHIOFENIUMU trifluoromethane sulfonate; Phenyl-screw (TORIKURORO methyl)-s-triazine, Halogen content compound system photo-oxide generating agents, such as methoxypheny-screw (TORIKURORO methyl)-s-triazine and naphthyl-screw (TORIKURORO methyl)-s-triazine; 1, 2-naphthoquinonediazide-4-sulfonyl chloride, 1, 2-naphthoquinonediazide-5-sulfonyl chloride, Diazoketone compound system photo-oxide generating agent; 4-tris phenacyl sulfones, such as a 1 of 2, 3, 4, and 4'-tetra-benzophenone, and 2-naphthoquinonediazide-4-sulfonate or 1, and 2-naphthoquinonediazide-5-sulfonate, Sulfonic-acid compound system photo-oxide generating agents, such as a mesityl phenacyl sulfone and screw (phenyl sulfonyl) methane; Benzoin tosylate, The tris trifluoromethane sulfonate of pyrogallol, nitrobenzyl -9, 10-diethoxy anthracene-2-sulfonate, The trifluoromethane sulfonyl bicyclo [2, 2, 1] hept-5-en -2, 3-JIKARUBO diimide, Sulfonic-acid compound system photo-oxide generating agents, such as N-hydroxysuccinimide trifluoromethane sulfonate, 1, and 8-naphthalene dicarboxylic acid imide trifluoromethane sulfonate, are mentioned. these compounds are independent -- it is -- two or more sorts can be combined and it can use.

[0022] Moreover, although a base can be generated by external stimulus, as an external stimulus, ultraviolet rays and heat are desirable, and the alt.nitrobenzyl carbamate, alpha, and alpha-dimethyl -3, 5-dimethoxy benzyl carbamates, acyloxy imino **, etc. can be illustrated as said latency base catalyst. Moreover, as a base generated by light, a hydrazine, a tetramethylenediamine, toluene diamine, diamino diphenylmethane, a hexa methyl tetra-amine, ammonia, monomethylamine, ethylamine, propylamine, a butylamine, hexylamine, cyclohexylamine, a DESHIRU amine, a cetyl amine, a piperidine, a piperazine, etc. are mentioned. Still more specifically [(2-nitrobenzyl) oxy-] Carbonyl] monomethylamine, [(2-nitrobenzyl) oxy-] Carbonyl] propylamine, [(2-nitrobenzyl) oxy-] Carbonyl] hexylamine, [(2-nitrobenzyl) oxy-] Carbonyl] cyclohexylamine, [(2-nitrobenzyl) oxy-] Carbonyl] aniline, a [(2-nitrobenzyl) oxy-] carbonyl] piperidine, [(2-nitrobenzyl) oxy-] Carbonyl] hexamethylenediamine, [(2-nitrobenzyl) oxy-] Carbonyl] phenylenediamine, [(2-nitrobenzyl) oxy-] Carbonyl] toluene diamine, [(2-nitrobenzyl) oxy-] Carbonyl] diamino diphenylmethane, [(2-nitrobenzyl) oxy-] Carbonyl] piperazine, [(2, 6-dinitro benzyl) oxy-] carbonyl] monomethylamine, [(2, 6-dinitro benzyl) oxy-] Carbonyl] propylamine, [(2, 6-dinitro benzyl) oxy-] Carbonyl] hexylamine, [(2, 6-dinitro benzyl) oxy-] Carbonyl] cyclohexylamine, [(2, 6-dinitro benzyl) oxy-] Carbonyl] aniline, [(2, 6-dinitro benzyl) oxy-] Carbonyl] piperidine, [(2, 6-dinitro benzyl) oxy-] Carbonyl] hexamethylenediamine, [(2, 6-dinitro benzyl) oxy-] Carbonyl] phenylenediamine, [(2, 6-dinitro benzyl) oxy-] Carbonyl] toluene diamine, [(2, 6-dinitro benzyl) oxy-] Carbonyl] diamino diphenylmethane, [(2, 6-dinitro benzyl) oxy-] Carbonyl] piperazine, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl monomethylamine, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl propylamine, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl hexylamine, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl cyclohexylamine, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl aniline, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl piperidine, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl hexamethylenediamine, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl phenylenediamine, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl toluene diamine, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl diamino diphenylmethane, [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl piperazine, A propionyl acetophenone oxime, a propionyl benzophenone oxime, Propionyl acetone oxime, a butyryl acetophenone oxime, A butyryl benzophenone oxime, butyryl acetone oxime, a horse mackerel POIRU acetophenone oxime, A horse mackerel POIRU benzophenone oxime, horse mackerel POIRU acetone oxime, a bitter taste roil acetophenone oxime, a bitter taste roil benzophenone oxime, bitter taste roil acetone oxime, etc. are mentioned. [(2-nitrobenzyl) oxy-] Carbonyl] cyclohexylamine, a [(2-nitrobenzyl) oxy-] carbonyl] hexamethylenediamine, and a [(alpha and alpha-dimethyl -3, 5-dimethoxy benzyl) oxy-] carbonyl hexamethylenediamine are mentioned especially. these compounds are

independent -- it is -- two or more sorts can be combined and it can use.

[0023] The operating rate of the (B) component in this invention constituent is 0.001 - 10 weight section to the (A) component 100 weight section (full hydrolysis condensate conversion), and is 0.01 - 10 weight section more preferably. (B) If the dielectric constant of a paint film does not become that the amount of the component used is under the 0.001 weight section with a sufficiently low value but the amount of the (B) component used exceeds 10 weight sections, the preservation stability of a solution may deteriorate.

[0024] (C) The boiling point in ordinary pressure is a solvent 180 degrees C or more, and the (C) component used for component this invention can mention polyhydric alcohol, a glycol system solvent, a glycol monoalkyl ether system solvent, a glycol dialkyl ethers solvent, a glycol monoalkyl ether ester solvent, a glycol diester system solvent, etc. As an example of these solvents, for example Ethylene glycol, 1,3-propanediol, 1, 2-propanediol, 1,4-butanediol, 1,3-butanediol, 1, 2-butanediol, 1,5-pentanediol, 1, 4-pentanediol, 1, 3-pentanediol, 1, 2-pentanediol, 1,6-hexanediol, 1, 5-hexandiol, 1, 4-hexandiol, 1, 3-hexandiol, 1, 2-hexandiol, 1, 7-heptane diol, 1, 2-heptane diol, 1, 8-octanediol, 1, 2-octanediol, 1, 9-nonane diol, 1, 2-nonane diol, 1, 10-Deccan diol, 1, 2-Deccan diol, 1, 12-dodecane diol, 1, 2-dodecane diol, 1, 14-tetradecane diol, 1, 2-tetradecane diol, 1, 16-hexadecane diol, 1, 2-hexadecane diol, 1, 18-OKUTA decane diol,

Since it became timeout time, translation result display processing is stopped.